

MONTOXYL BARNIZ ACQUA SATINADO



FAMILY MADERA / SISTEMAS TINTOMÉTRICOS
LINE BARNICES (AGUA)

DESCRIPTION AND NATURE

One-component, water-based acrylic finish. Fast-drying. Especially suitable for varnishing indoor/outdoor furniture and wood under a cover (CU2). Excellent feel and transparency.

USAGES

In new and used woods.
 On new wood and unvarnished wood derivatives. Especially suitable for indoor use.
 Suitable for furniture and doors
 Ideal for general carpentry.
 Solid Wood and Veneer

PROPERTIES

- Waterproof
- Transparence
- Does not alter support tone once dry
- Low odour
- Very robust and resistant
- Non Yellowing
- Good performance
- Water-based
- Drying fast
- Good applicability
- Good thixotropy that facilitates vertical application

TECHNICAL CHARACTERISTICS

Referencia Color	MONTOXYL BARNIZ ACQUA SATINADO
Finish	Satin
Specific weight	(1.020 ± 0.010)g/mL
Viscosity	(70 ± 10)s
Solids in volume	(31 ± 1)
Solids in weight	(33 ± 1)
VOC	Cat. e/BA 150/130 (2007/2010):77,53 g/l
Aproximated performance by coat	10-14 m²/L

Dry to touch	(20°C; HR: 60%):30-60min
Dry to repaint	(20°C; HR: 60%):3-24h
Colours	Transparente 900

Cartas Montoxyl Barnices y Montoxyl Lasures.

SURFACE PREPAIRING

New surfaces

New wood:

1. The substrate must be free of foreign matter and/or residue.
2. Apply to wood with a moisture content of less than 12%.
3. Apply to healthy, well-degreased, dust-free, and dry wood.
4. Sand and remove any glue residue from joints and machining defects.

######

MONTOXYL BARNIZ ACQUA SATINADO



Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 18 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 4 L