

Fecha de Alta

01-02-2008

Versión

7 - 22/08/2024



FAMILY LINE

ANTIHUMEDAD E IMPERMEABILIZAC.

IMPERMEABILIZACION HORIZONTAL

DESCRIPTION AND NATURE

Rough-texture primer, adhesive bridge for waterproofing paints used on terraces and roofs. Facilitates the distribution and adhesion of subsequent coats of waterproofing paint, as well as the laying of fibreglass mesh.

USAGES

Outdoor/Indoor

Cement

Brick

Catalan tile

Asphalt fabric

Specific Koraza Top Cover or Montokril Elastómero type primer for waterproofing

PROPERTIES

Adherence

Does not present tacking

Does not spread flame

Improve the adherence between coats of Koraza Top Cover, Montokril Elastomero, and other similar products

Improve the application between coats, by avoiding the roller slideness

Do avoid wrinkles in the mesh

It is adaptable over the surface deffectives

It saves time when using elastics

Easy repair

TECHNICAL CHARACTERISTICS

Referencia Color PRIMER KORAZA ROJO 152

Finish Smooth slightly sanded

Specific weight $1,47 \pm 0,05$ kg/l

Viscosity 150 +/- 20 PO

Solids in volume 47 ± 1 Solids in weight 66 ± 1

VOC Cat. g/BA 50/30 (2007/2010):0,73 g/l

Aproximated performance by coat 4-8 m²/L

Dry to touch (20°C HR:60%):1-2h

Dry to repaint (20°C HR:60%):4-6h

Colours Red 152

SURFACE PREPAIRING

New surfaces

Cement mortar:

1. Wait until completely set (minimum 30 days).
2. Use an abrasive jet to remove any potential efflorescence from the base and neutralise alkaline surfaces.
3. Sand down highly polished surfaces to open up the mortar.
4. Remove any strange products and/or residues from the base.
5. Use outdoor plaster to fill any defects in the base (In family 6 see PREPARING BASES lines corresponding to powder plaster and prepared fillers to select a suitable solution).
6. Sand down highly polished surfaces to open up the mortar.

Fecha de Alta

01-02-2008

Versión

7 - 22/08/2024

7. Apply Fijamont to any cement mortar surfaces so that it does not come into contact with Tejamont Top Cover or Montokril Elastómero.

Asphalt shingles:

1. Check adhesion and clean up non-adhesive areas, identifying points where the anchoring is weak. Carry out adhesion tests.
2. Treat mouldy bases with Monto Limpia Moho.

Brick:

1. Remove any strange products and/or residues from the base.
2. Use outdoor plaster to fill any defects in the base (In family 6 see PREPARING BASES lines corresponding to powder plaster and prepared fillers to select a suitable solution).
3. Treat mouldy bases with Monto Limpia Moho.

Restoring and maintenance

1. Completely remove any old paint that is flaking or in poor condition.
2. Dull down glossy surfaces to ensure good adhesion.
3. For painted bases, check the solidity, adhesion and nature of the paint to avoid possible incompatibilities and clear off any dust and dirt before repainting.
4. Use outdoor plaster to fill any defects in the base (In family 6 see PREPARING BASES lines corresponding to powder plaster and prepared fillers to select a suitable solution).
5. Treat mouldy bases with Monto Limpia Moho.

WAY OF USE

Application notes

- Clean the surface, getting rid of any dirt, moss, mould etc. and wash with clean, uncontaminated water.
- Stir the product until perfectly homogenised.
- Dilute the product according to the porosity and state of the base.
- It is very important that the temperature of the base be above 5°C, otherwise the product may freeze.
- Do not apply the product at temperatures below 5°C or above 35°C.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	20-40%
Roller	20-40%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Support with mould			
MAX	Monto Limpia Moho + Fijamont + Primer Koraza	Malla de fibra + Koraza Top Cover	Koraza Top Cover
STD	Monto Limpia Moho + Fijamont + Primer Koraza	Montokril Elastómero	Montokril Elastómero
Old paintings in bad state			
MAX	Fijamont + Primer Koraza	Malla de fibra + Koraza Top Cover	Koraza Top Cover
STD	Primer Koraza	Montokril Elastómero	Montokril Elastómero
Asphalt fabric			
MAX	Primer Koraza	Malla de fibra + Koraza Top Cover	Koraza Top Cover
STD	Primer Koraza	Montokril Elastómero	Montokril Elastómero
Brickwork			
MAX	Primer Koraza	Malla de fibra + Koraza Top Cover	Koraza Top Cover
STD	Primer Koraza	Montokril Elastómero	Montokril Elastómero

Fecha de Alta

01-02-2008

Versión

7 - 22/08/2024

Support weak

MAX	Fijamont + Primer Koraza	Malla de fibra + Koraza Top Cover	Koraza Top Cover
STD	Fijamont + Primer Koraza	Montokril Elastómero	Montokril Elastómero

Project

MAX	Fijamont + Primer Koraza	Malla de fibra + Koraza Top Cover	Koraza Top Cover
STD	Primer Koraza	Montokril Elastómero	Montokril Elastómero

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

12 L