502057

Fecha de Alta 29-06-2023 Versión

ACRIPOL PISCINAS POLIESTER AZUL



3 - 04/09/2025



PRODUCTOS PARA USO ESPECIFICO **FAMILY PISCINAS** LINE

DESCRIPTION AND NATURE

High resistance two-component polyurethane paint developed for painting polyester pools.

USAGES

Indoors/Outdoors Polyesther Fibre

PROPERTIES

Water resistant

Excellent gloss mainteinance

The product may become discoloured depending on the type and concentration of the disinfectant used.

Chemical resistence

Very decorative aesthetic finish

Excellent adhesion

For both freshwater and saltwater pools

TECHNICAL CHARACTERISTCS

Don't be made that	0.41-
Dry to touch	30-60min
Aproximated performance by coat	5-9 m ² /L
Solids in weight	66± 1
Solids in volume	50± 1
Viscosity	207 +/- 30 SG
Specific weight	1,33± 0,05 kg/l
Mixture relation	4:1 en volumen
Referencia Color	ACRIPOL PISCINAS POLIESTER AZUL

Dry to touch	30-60min
Dry to repaint	24h
Colours	Blue

SURFACE PREPAIRING

New surfaces

Remove any dirt, formwork agents, grease and oil. Gently sand down the surface. Remove the sanding dust.

Restoring and maintenance

Remove poorly adhered and defective parts. Gently sand down the surface. Remove the sanding dust.

WAY OF USE

Application notes

To apply following the dilution recommendations. Not to apply to high temperature nor with high relative humidity. To apply fine layers

502057

Fecha de Alta 29-06-2023 Versión

ACRIPOL PISCINAS POLIESTER AZUL



3 - 04/09/2025

To fulfill the effective legislation.

Minimum recommended time for filling the pool 8 days.

This product is resistant to chlorine and chlorine derivatives if concentration is within the limits indicated in RD 742/2013, 27th of September. For any other treatment (flocculants, algaecides ...), check with the supplier the possibility to be used in painted pools.

Solvent for dilution and cleaning

Solvent 1410

Way of use Aproximate dilution

 Air-less gun
 0 - 20 %

 Spray gun
 10 - 30 %

 Brush, Roller
 0 - 15 %

SYSTEM

Procedures depending of surface type

Trocedures depending of surface type						
	Primer	Intermedium	Finish			
Polyester swimming pools						
MAX						
STD	Acripol piscinas poliéster		Acripol piscinas poliéster			

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time: 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adecuate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

3.2 L