



FAMILY INSTALACIONES DEPORTIVAS

LINE PISCINAS

DESCRIPTION AND NATURE

Chlorinated rubber paint for swimming pools with perfect adhesion and high transpiration.

USAGES

Outdoor/Indoor
Cement
Mortar
Cement
Concrete
Swimming pool
Pools

PROPERTIES

Waterproof
Water resistant
Alcalynity resistance
The product may become discoloured depending on the type and concentration of the disinfectant used.
Drying fast
Excellent adhesion

TECHNICAL CHARACTERISTICS

Referencia Color	MONTOSPORT PISC. NEREIDA AL CLOROC. AZUL
Specific weight	1,34± 0,05 kg/l
Viscosity	75 +/- 5 KU
Solids in volume	41± 1
Solids in weight	63± 1
Aproximated performance by coat	5-7 m ² /L
Dry to touch	10-30 min. Filling the pool: 7 days
Dry to repaint	24h minimum
Colours	Blue 183

SURFACE PREPAIRING

New surfaces

Cement mortar:

- Wait until completely set (30 days minimum).
- Use an abrasive jet to remove any potential efflorescence from the base and neutralise alkaline surfaces.
- Sand down highly polished surfaces to open the pores. If treating the surface with hydrochloric acid (diluted 10% in water) to open the pores, clean with abundant water before painting.
- Dilute the product according to the porosity and state of the base. It is always advisable to apply a very diluted first coat.
- Remove any foreign bodies and/or residues from the surface.

Restoring and maintenance

Completely remove old paints in poor condition or that are poorly adhered using a steel brush, scraper or other mechanical means.

For painted bases, check the solidity and adhesion of the old paint, and identify the type of paint to avoid possible incompatibilities. Remove any dust and dirt before repainting.

It is not recommended to apply it over water-based swimming pool paint.

Glossy surfaces should be dulled down to ensure good adhesion.
Walls with mildew should first be treated with Montolimp.

WAY OF USE

Application Notes

Apply onto clean and dry surfaces. Stir until it is perfectly uniform and apply once the product has been properly diluted. This product is resistant to chlorine and chlorine derivatives if concentration is within the limits indicated in RD 742/2013, 27th of September.
For any other treatment (flocculants, algacides ...), check with the supplier the possibility to be used in painted pools.

Solvent for dilution and cleaning

Way of use	Aproximate dilution
Air-less gun	5-20% MÁX
Air-mix gun	5-20% MÁX
Aerographic gun	5-20% MÁX
Low pressure turbo	5-20% MÁX
Brush, Roller	5-15% MÁX

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Support with mould			
MAX	MONTOLIMP Y FIJAMONT	MONTOSPORT PISC. NEREIDA AL CLOROC DILUIDO	MONTOSPORT PISC. NEREIDA AL CLOROC
STD	MONTOLIMP Y FIJAMONT	MONTOSPORT PISC. NEREIDA AL CLOROC DILUIDO	MONTOSPORT PISC. NEREIDA AL CLOROC
Old paintings in bad state			
MAX	ELIMINAR Y PROCEDER COMO EN BUEN ESTADO		MONTOSPORT PISC. NEREIDA AL CLOROC.
STD	ELIMINAR Y PROCEDER COMO EN BUEN ESTADO		MONTOSPORT PISC. NEREIDA AL CLOROC.
Old painting in good state			
MAX	MONTOSPORT PISC. NEREIDA AL CLOROC. DILUIDO		MONTOSPORT PISC. NEREIDA AL CLOROC.
STD			
Support weak			
MAX	FIJAMONT	MONTOSPORT PISC. NEREIDA AL CLOROC. DILUIDO	MONTOSPORT PISC. NEREIDA AL CLOROC.
STD	FIJAMONT	MONTOSPORT PISC. NEREIDA AL CLOROC. DILUIDO	MONTOSPORT PISC. NEREIDA AL CLOROC.
New cements and By-products			
MAX	FIJAMONT	MONTOSPORT PISC. NEREIDA AL CLOROC. DILUIDO	MONTOSPORT PISC. NEREIDA AL CLOROC.
STD	MONTOSPORT PISC. NEREIDA AL CLOROC. DILUIDO	MONTOSPORT PISC. NEREIDA AL CLOROC. DILUIDO	MONTOSPORT PISC. NEREIDA AL CLOROC.

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS