

Fecha de Alta

26-02-2014

Versión

13 - 08/06/2020



FAMILY

CREA

LINE

MADERA EXTERIOR

DESCRIPTION AND NATURE

"Woodstain"-type water protector, developed with nano-particle technology, for protection of interior / exterior wood, reinforced with U.V. protection agents. Maximum colour protection.

USAGES

Outdoors/Indoors

For maximum protection, finish in colour.

Apply a maximum of 275 +/- 25 g/m²

Recommended in high mountain and coastal areas for porous finishes, repaintable with water-based woodstain.

PROPERTIES

- Penetration power
- Provides open pore finish
- Do not apply white media, you can amarillarlos slightly, but does not alter the properties of the product.
- Does not turn yellow
- no need of sanding, but easy to do once dried
- Recommended number of coats : 2-3 coats over new wood, 1-2 coats as maintenance
- No cracking at all
- Does not form blisters
- Water steam transpirable
- Odourless when dry
- Endures brusque changes in the weather
- Flexible
- Microporous
- Highlights the wood's natural grain
- U.V. resistant
- May be used as a base when diluted, thus nourishing the wood

TECHNICAL CHARACTERISTICS

Referencia Color	CREA LASURE SATINADO INCOLORO
Finish	Satin
Specific weight	0,98± 0,05 kg/l
Viscosity	18 +/- 2 PO
Solids in volume	20± 1
Solids in weight	23± 1
VOC	Cat. e/BA 150/130 (2007/2010):4,71 g/l
Aproximated performance by coat	10-16 m ² /L
Dry to touch	(20°C HR:60%): 2-4 h. Total: 12-24 h
Dry to repaint	(20°C HR:60%): 12-24 h
Colours	Colors: Pine, Oak, Walnut, Rosewood, Chestnut, Teak, Mahogany. Colorless, to reduce intensity of tones. Cromiservice and Montomix systems (max 5%). Montotinte universal or water (max: 5%)

SURFACE PREPAIRING

Fecha de Alta

26-02-2014

Versión

13 - 08/06/2020

New surfaces

New woods.

- Outdoors, protect the wood with Klearxyl Di Anticarcomas from attack by fungi and xylophagous insects.
- The support must be free of foreign products and / or residues.
- Apply on wood with a moisture content of less than 20%.
- Apply on healthy, well-degreased, dust-free and dry woods.
- Sand and eliminate possible glue residues in the assemblies and machining failures.
- If the wood shows signs of aging, it must be previously sanded and dust removed by brushing or any other mechanical means.
- Applying the CREA LASURE SATINADO in the exposed conditions, and following the indications of restoration and maintenance, the product can provide the wood with a protection of maximum observed resistance of up to 7 years. Always, depending on the location / area, conditions and attacks to which the varnished wood is subjected.

Restoring and maintenance

Varnished or painted woods:

- If they have been varnished with open-pore lasures: Remove foreign products, remove poorly adhered or poorly maintained areas, sand lightly, remove the dust resulting from sanding and proceed as on new woods.
- If they have been varnished with closed pore varnishes or the like, sand thoroughly and if necessary remove by stripping or by mechanical means and proceed as on new woods.
- If they have been varnished with cellulose or polyurethane varnishes, remove by stripping or by mechanical means and proceed as on new woods.
- If they have been enameled with synthetic enamels, remove by pickling or by mechanical means, sand until wood is reached and proceed as on new woods.
- Outdoors, protect the wood with Klearxyl Di Anticarcomas from attack by fungi and xylophagous insects.
- In parts already varnished with CREA LASURE SATIN FINISH and in order to maintain all their protective efficacy, it is advisable to periodically check the condition / appearance of the surfaces. If deterioration is observed, by impacts and / or scratches, etc. We recommend sanitizing and sanding the damaged area and coating with CREA LASURE SATINADO.

WAY OF USE

Application notes

- Stir the product until it is perfectly homogenized.
- Apply on clean and dry substrates.
- Apply following the dilutions recommended in the Application Systems section.
- Pre-sand to guarantee a good penetration and leveling on the wood.
- In the first hand, it is advisable to prime preferably with CREA Impregnante.
- Do not apply the product at high temperatures, or on surfaces exposed to strong insolation.
- Maintain good ventilation conditions during the drying time.
- Do not apply with relative humidity higher than 80%

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	fondo: 10-30%
Roller	10-30%
Air-less gun	30-50%
Air-mix gun	30-50%
Aerographic gun	10-30%
Low pressure turbo	10-30%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Open pore varnished wood			
MAX	Exterior: Decapar+ Anticarcomas Klearxyl Di	Crea Impregnante Color	Crea Lasure Satinado Color
STD	Exterior: Decapar+ Anticarcomas Klearxyl Di	Crea Impregnante Color	Crea Lasure Satinado Incoloro/Color

Fecha de Alta

26-02-2014

Versión

13 - 08/06/2020

New /old wood indoor/outdoor

MAX	Exterior: Anticarcomas Klearxyl Di	Crea Impregnante Color	Crea Lasure Satinado Color
STD	Exterior: Anticarcomas Klearxyl Di	Crea Impregnante Color	Crea Lasure Satinado Incolor/Color

Painted or varnished wood (closed pore) outdoor

MAX	Exterior: Anticarcomas Klearxyl Di	Crea Impregnante Color	Crea Lasure Satinado Color
STD	Exterior: Anticarcomas Klearxyl Di	Crea Impregnante Color	Crea Lasure Satinado Incoloro/Color

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.5 L, 2.5 L