

CREA BARNIZ ULTRA BRILLANTE



FAMILY

CREA

LINE

MADERA INTERIOR

DESCRIPTION AND NATURE

Aliphatic acrylic-urethane varnish for the protection and decoration of indoor / outdoor wood under cover (CU2). Excellent transparency. To apply on floors, parquets, furniture, railings, ... with nanoadditives, it creates a waterproof layer of maximum hardness and resistance to shocks, abrasion and wear. Good resistance to household chemicals. Highlights the wood grain. Very easy application and low odor.

USAGES

Indoors

Indoor / Outdoor under cover (CU2)

Wood previously primed with Crea Impregnante Color

Wood

Recommended previously created with primer

Suitable for furniture and doors

Suitable for parquet and wooden floors

Use over clean woods

Apply a maximum of 110 +/- 20 g/m² per coat.

PROPERTIES

- Strongness
- Waterproof
- Surface protection
- Transparency
- Odourless when dry
- Resistance to friction and hits
- Resistant to washing
- Easily applicable
- Water-based
- Drying fast
- Dust-proof

TECHNICAL CHARACTERISTICS

Referencia Color	CREA BARNIZ ULTRA BRILLANTE INCOLORO
Finish	Gloss
Specific weight	1,05 ± 0,05 kg/l
Viscosity	55 +/- 5 SG
Solids in volume	22 ± 1
Solids in weight	26 ± 1
VOC	Cat. i/BA 140/140 (2007/2010): 76,55 g/l
Aproximated performance by coat	6-9 m ² /L
Dry to touch	30 - 60 min.
Dry to repaint	12 - 24 h.
Colours	Colorless

SURFACE PREPAIRING

New surfaces

New woods.

CREA BARNIZ ULTRA BRILLANTE

- The support must be free of foreign products and / or residues.
- Apply on wood with a moisture content of less than 20%.
- Apply on healthy, well-degreased, dust-free and dry woods.
- Sand and eliminate possible glue residues in the assemblies and machining failures.
- If the wood shows signs of aging, it must be previously sanded and dust removed by brushing or any other mechanical means.

Restoring and maintenance

Varnished or painted woods:

- If they have been varnished with open-pore lasures: Remove foreign products, remove poorly adhered or poorly maintained areas, sand lightly, remove the dust resulting from sanding and proceed as on new woods.
- If they have been varnished with closed pore varnishes or the like, sand thoroughly and if necessary remove by stripping or by mechanical means and proceed as on new woods.
- If they have been varnished with cellulose or polyurethane varnishes, remove them by pickling or by mechanical means and proceed as on new woods.
- If they have been enameled with synthetic enamels, remove by pickling or by mechanical means, sand until wood is reached and proceed as on new woods.

WAY OF USE

Application notes

- Stir the product until it is perfectly homogenized.
- Apply on clean and dry substrates.
- Apply following the dilutions recommended in the Application Systems section.
- Pre-sand to guarantee a good penetration and leveling on the wood.
- Do not apply the product at high temperatures, or on surfaces exposed to strong insolation.
- Maintain good ventilation conditions during the drying time.
- Do not apply with relative humidity higher than 80%

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	0 - 10%
Roller	0 - 20 %
Air-mix gun	0 - 5 %
Spray gun	0 - 20 %

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Indoor wood			
MAX	Crea Impregnante Incoloro/Color y/o Antitaninos	Crea Barniz Ultra Brillo/Satinado/Mate	Crea Barniz Ultra Brillo/Satinado/Mate
STD	Crea Impregnante Incoloro/Color		Crea Barniz Ultra Brillo/Satinado/Mate

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

CREA BARNIZ ULTRA BRILLANTE

NOTE

Maximum recommended storage time : 18 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.5 L, 2.5 L