

MONTO MASILLA SUPERLIGERA



FAMILY PREPARACIONES, FONDOS E IMPR.

LINE MASILLAS AL USO

DESCRIPTION AND NATURE

Light filler. Ideal for quick repairs to cracks, holes, etc.
0% shrinkage, very thick consistency and high filling capacity.

USAGES

Outdoor/Indoor

Walls made of brick or other materials that tend to leave marks or stains when painted

Concrete

Brick

Cement mortars

Plaster

Wood

PROPERTIES

Acoustic insulator
Thermal insulator
Low thermal conductivity
Energy saving
Anticondensation
Fast drying
Outdoor resistance
Easy to sand
Does not fall off base

TECHNICAL CHARACTERISTICS

Referencia Color	MONTO MASILLA SUPERLIGERA
Finish	Matt
Specific weight	0,6± 0,05 kg/l
Solids in volume	65± 1
Solids in weight	45± 1
Minimum recommended thickness	Ilimitado
Aproximated performance by coat	Depending of product usage
Dry to touch	(20°C HR: 60%): 1h
Dry to repaint	(20°C HR: 60%): 1-4h
Colours	White 103

SURFACE PREPARING

New surfaces

Cement/plaster mortar:

- Check the suitability of the filler for the base.
- Wait until fully hardened (at least 30 days).
- Clean any efflorescence off the base, and neutralise alkaline surfaces.
- On extremely smooth surfaces, sand lightly for tooth.
- Clean any foreign products and/or residue from the base.
- Open up any cracks or fissures until you reach a sound base, brush off the dust, and apply the filler or plaster as shown in the sections Application Systems and Application.
- Do not apply thicker coats than the recommended maximum.

MONTO MASILLA SUPERLIGERA



Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 4 L



FAMILY LINE

DESCRIPTION AND NATURE

Light filler. Ideal for quick repairs to cracks, holes, etc.
0% shrinkage, very thick consistency and high filling capacity.

USAGES

PROPERTIES

- Acoustic insulator
- Thermical insulator
- Low thermical conductivity
- Energy saving
- Anticondensation
- Fast drying
- Outdoor resistance
- Easy to sand
- Does not fall off base

TECHNICAL CHARACTERISTICS


Referencia Color

Finish	Matt
Specific weight	0,6± 0,05 kg/l
Solids in volume	65± 1
Solids in weight	45± 1

Minimum recommended thickness	Ilimitado
Aproximated performance by coat	Depending of product usage

Dry to touch	(20°C HR: 60%): 1h
Dry to repaint	(20°C HR: 60%): 1-4h
Colours	White 103

MONTO MASILLA SUPERLIGERA



SURFACE PREPAIRING

New surfaces

Cement/plaster mortar:

- Check the suitability of the filler for the base.
- Wait until fully hardened (at least 30 days).
- Clean any efflorescence off the base, and neutralise alkaline surfaces.
- On extremely smooth surfaces, sand lightly for tooth.
- Clean any foreign products and/or residue from the base.
- Open up any cracks or fissures until you reach a sound base, brush off the dust, and apply the filler or plaster as shown in the sections Application Systems and Application.
- Do not apply thicker coats than the recommended maximum.
- On extremely crumbly surfaces, before applying the filler, fix it with the appropriate fixative.

Restoring and maintenance

- Remove products from the base which are flaking or in poor condition, and raise a tooth on smooth surfaces by sanding or other mechanical means.
- Check the adhesion and treat as for new BASES.

WAY OF USE

Application notes

- Using the tools shown in the application system, clean and free of rust.
- Apply enough for the first coat.
- It is possible to increase the number of coats to 3 or more to obtain a thicker layer, up to 15 mm .
- Repaint after the indicated drying time. As this depends on humidity, temperature and the thickness of the applied product, when the product no longer clogs up sandpaper, this will mean it is ready to paint.

Solvent for dilution and cleaning

Water

Way of use

Aproximate dilution

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
New work			
MAX	Montó imprimación Universal	Montó Masilla al Uso Súper Ligera	Pintura Plástica Montó
STD	Montó Masilla al Uso Súper Ligera		Pintura Plástica Montó
Wood			
MAX	Selladora	Montó Masilla al Uso Súper Ligera	Pintura Plástica Montó
STD		Montó Masilla al Uso Súper Ligera	Pintura Plástica Montó
Support weak			
MAX	Montó imprimación Universal	Montó Masilla al Uso Súper Ligera	Pintura Plástica Montó
STD	Montó Masilla al Uso Súper Ligera		Pintura Plástica Montó
Asphalt fabric			
MAX	Montó Masilla al Uso Súper Ligera	Montó Masilla al Uso Súper Ligera	Pintura Plástica Montó
STD		Montó Masilla al Uso Súper Ligera	Pintura Plástica Montó
Old paintings in bad state			

682298


MONTO MASILLA SUPERLIGERA

Fecha de Alta

06-09-2022

Versión

4 - 29/01/2026



MAX Eliminar + Fijador

Montó Masilla al Uso Súper Ligera

Pintura Plástica Montó

STD Eliminar

Montó Masilla al Uso Súper Ligera

Pintura Plástica Montó

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

PACKINGS

0.75 L, 4 L