

ACRIPOL PISCINAS POLIESTER AZUL



FAMILY

PRODUCTOS PARA USO ESPECIFICO

LINE

PISCINAS

DESCRIPTION AND NATURE

High resistance two-component polyurethane paint developed for painting polyester pools.

USAGES

Indoors/Outdoors

Polyester

Fibre

PROPERTIES

Water resistant

Excellent gloss maintainance

The product may become discoloured depending on the type and concentration of the disinfectant used.

Chemical resistance

Very decorative aesthetic finish

Excellent adhesion

For both freshwater and saltwater pools

TECHNICAL CHARACTERISTICS

Referencia Color	ACRIPOL PISCINAS POLIESTER AZUL
Mixture relation	4:1 en volumen
Specific weight	1,33± 0,05 kg/l
Viscosity	207 +/- 30 SG
Solids in volume	50± 1
Solids in weight	66± 1
Aproximated performance by coat	5-9 m ² /L

Dry to touch	30-60min
--------------	----------

Dry to repaint	24h
----------------	-----

Colours	Blue
---------	------

SURFACE PREPAIRING

New surfaces

- Remove any dirt, formwork agents, grease and oil.
- Gently sand down the surface.
- Remove the sanding dust.

Restoring and maintenance

- Remove poorly adhered and defective parts.
- Gently sand down the surface.
- Remove the sanding dust.

WAY OF USE

Application notes

- To apply following the dilution recommendations.
- Not to apply to high temperature nor with high relative humidity.
- To apply fine layers.

- To fulfill the effective legislation.
- Minimum recommended time for filling the pool 8 days.
- This product is resistant to chlorine and chlorine derivatives if concentration is within the limits indicated in RD 742/2013, 27th of September. For any other treatment (flocculants, algacides ...), check with the supplier the possibility to be used in painted pools.

Solvent for dilution and cleaning

Solvent 1410

Way of use	Aproximate dilution
Air-less gun	0 - 20 %
Spray gun	10 - 30 %
Brush, Roller	0 - 15 %

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Polyester swimming pools			
MAX			
STD	Acripol piscinas poliéster		Acripol piscinas poliéster

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

3.2 L