

Fecha de Alta

18-02-2008

Versión

1C - 13/11/2025


FAMILY ANTIHUMEDAD E IMPERMEABILIZAC.

LINE IMPERMEABILIZACION VERTICAL

DESCRIPTION AND NATURE

Water based transparent varnish, specially formulated for the protection of porous and absorbent surfaces. It does not alter practically the aspect of the support. You must avoid excesses of product that forms film.

USAGES

Outdoors/Indoors

Brick

Stone

Exposed brickwork

Fibre-cement

Cement mortars

Concrete

PROPERTIES

Water-resistant

Does not alter support tone once dry

Do protect the varnished surfaces from atmospherical factors

To fix the dusty surfaces

Porosity regulator

Does not spread flame

TECHNICAL CHARACTERISTICS

Referencia Color	BARNIZ LADRILLO MATE
Finish	Transparent
Specific weight	0,98± 0,05 kg/l
Viscosity	35 +/- 8 SG
Solids in volume	18± 1
Solids in weight	19± 1
VOC	Cat. c/BA 75/40 (2007/2010): 16,24 g/l
Aproximated performance by coat	9-15 m ² /L
Dry to touch	(20°C HR: 60%): 30-60min
Dry to repaint	(20°C HR: 60%): 8h
Colours	Colourless

SURFACE PREPARING
New surfaces

- 1 -Remove off any efflorescences, remains or foreign products by abrasive jet and neutralize alkaline surfaces.
- 2 -Extremely polished surfaces should be sanpapered to open pores.
- 3 -Cover surface imperfections with suitable plaster.
- 4 -Mildewed surfaces should be treated with Monto Limpia Moho.

Restoring and maintenance

1. This product should only be applied on surfaces free of any paint trace and with open porous.
2. For old surfaces that comply with these requirements, proceed as per new surfaces.

Fecha de Alta

18-02-2008

Versión

1C - 13/11/2025

WAY OF USE

Application notes

- Shake product until perfectly homogenized.
- Dilute the product from 100 to 25% in water. The bigger the porous, is the less thinning needs. Excess of product may cause glossy areas.
- This product should not be applied at temperatures below 5°C or any surfaces which have been in the sun.

Solvent for dilution and cleaning

Water

Way of use

Painting brush

Roller

Air-less gun

Air-mix gun

Aerographic gun

Low pressure turbo

Aproximate dilution

1:1 en agua primera mano/4 barniz: 1 agua siguientes

1:1 en agua primera mano/4 barniz: 1 agua siguientes

1:1 en agua primera mano/4 barniz: 1 agua siguientes

1:1 en agua primera mano/4 barniz: 1 agua siguientes

1:1 en agua primera mano/4 barniz: 1 agua siguientes

1:1 en agua primera mano/4 barniz: 1 agua siguientes

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Support with mould			
MAX	Monto Limpia Moho	Barniz Ladrillo	Barniz Ladrillo + Monto Aditivo con conservante antimoho
STD	Monto Limpia Moho		Barniz Ladrillo + Monto Aditivo con conservante antimoho
Old paintings in bad state			
MAX	Eliminar antiguas pinturas	Barniz Ladrillo	Barniz Ladrillo
STD	Eliminar antiguas pinturas		Barniz Ladrillo
Brickwork			
MAX	Barniz Ladrillo		Barniz Ladrillo
STD	Barniz Ladrillo		Barniz Ladrillo
Support weak			
MAX	Fijamont, Emulsión Fijadora	Barniz Ladrillo	Barniz Ladrillo
STD	Fijamont, Emulsión Fijadora		Barniz Ladrillo
Masonry mortar			
MAX	Fijamont, Emulsión Fijadora	Barniz Ladrillo	Barniz Ladrillo
STD	Barniz Ladrillo		Barniz Ladrillo
Artificial stone, bricks , and porous roofing tiles			
MAX	Barniz Ladrillo		Barniz Ladrillo
STD	Barniz Ladrillo		Barniz Ladrillo

SECURITY

Fecha de Alta

18-02-2008

Versión

1C - 13/11/2025

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 4 L, 12 L