

Fecha de Alta

13-08-2021

Versión

4 - 08/01/2026



**FAMILY** ESMALTES

**LINE** SPRAY MULTISOPORTE

### DESCRIPTION AND NATURE

Anti-rust acrylic primer in solvent medium based on pure Zinc, applicable on galvanised metal, iron, steel and its derivatives, repaintable with synthetic and acrylic enamels, for interior and exterior.

### USAGES

Indoors/Outdoors

Metal

### PROPERTIES

Based with pure zinc powder, minimum at 96%

Good coverage

Strong resistance to the atmospherical factors

Drying fast

Good anti-corrosive protection

Good anchor

### TECHNICAL CHARACTERISTICS

Referencia Color MONTOSPRAY PRIMER ZINK

Aproximated performance by coat Depending of product usage

Dry to touch 15min

Dry to repaint 1-2h

### SURFACE PREPARING

#### New surfaces

Iron, derived metals and other metals:

- The surface must be free of foreign products and/or residues.
- The surface must be degreased, clean and dry.
- On rusty surfaces, we must eliminate the rust by the usual means recommended by Montó with any rust inhibitor manufactured by our Company, which should be applied in advance.
- We must protect the areas that we do not want to paint.
- Eliminate, in general, products that are poorly adhered or in poor condition.

#### Restoring and maintenance

Iron and enamelled derivatives:

1. On paints in good condition, sand to open the pore, checking that the adherence is perfect.
2. On paints in bad condition, remove it by mechanical or chemical means and proceed as if it were a new surface.

### WAY OF USE

#### Application notes

- Shake the container vigorously for about 2 minutes to homogenise its contents perfectly.
- Carry out application tests in a non-visible place.
- Protect areas that are not to be painted.
- Apply at a distance of 25-30cm from the surface in light, criss-cross strokes.
- Do not apply the product at high temperatures, or on surfaces exposed to strong sunlight.
- Maintain good ventilation conditions during the drying time.
- Do not apply while the relative humidity is above 80%.
- Do not use at temperatures below 15°C.

Fecha de Alta

13-08-2021

Versión

4 - 08/01/2026

- When finished, empty the contents of the cannula by dosing with the container upside down.
- Approximate yield per 400ml container 1-1,2 m<sup>2</sup> (two cross-coats).

**Solvent for dilution and cleaning**

Solvent 1406-05

**Way of use****Aproximate dilution****SYSTEM****Procedures depending of surface type**

	Primer	Intermedium	Finish
<b>Metal</b>			
<b>MAX</b>	Montospray Primer Zink	Montospray Primer Zink	Acabados Montó
<b>STD</b>	Montospray Primer Zink		Acabados Montó

**SECURITY**

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

**NOTE**

Maximum recommended storage time : 48 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

**PACKINGS**

0.4 L