

MONTO PUENTE DE UNIÓN TACK



FAMILY LINE

PREPARACIONES, FONDOS E IMPR.

IMPRIMACIONES PAREDES-FACHADAS

DESCRIPTION AND NATURE

Water-based adhesive primer with extended tack. Bonding agent between mortars on absorbent construction surfaces.

USAGES

Walls and ceilings
Indoors/Outdoors
Stone
Undamaged rough mortar coats.
Plaster finishing
Absorbent supports
Cement, Plaster, Concrete, Brick
Cementitious mortars and anhydrite supports
Fibre-cement
It enables the adhesion of leveling and rendering mortars to porous substrates

PROPERTIES

- Penetrating depth
- Ready for use
- Good applicability
- Mortar bonding bridge
- Stickiness
- Long open time
- Adhesion on a wide range of surfaces

TECHNICAL CHARACTERISTICS

Referencia Color	MONTO PUENTE DE UNIÓN TACK
Finish	Transparent
Specific weight	(1,01±0,01) kg/l
Viscosity	(20±2) PO
Solids in volume	39±1
Solids in weight	39±1
VOC	Cat. h/BA 50/30 (2007/2010):0,00 g/l
Aproximated performance by coat	6-10 m²/L
Dry to touch	30min
Classification	AFNOR: NFT. 36005 - Famille I. Classe 7b2

SURFACE PREPAIRING

New surfaces

- In freshly applied mortars, it is necessary to allow the materials to set and dry completely.
- Clean the substrate of any foreign matter and/or residue.
- The substrate must be dry, clean, and free of dust, particles, oils, or any other particles that could impair the adhesion of the material to the substrate.

Restoring and maintenance

This product is intended to be used as an intermediate layer and not as a finish, therefore no restoration or maintenance

recommendations are included.

WAY OF USE

Application notes

- Do not use on slabs or floors. Also avoid use on structural joints.
- Stir the product until completely homogeneous. Then apply with a brush or roller.
- Apply to clean, dry or slightly damp substrates, but never waterlogged.
- It is important to control the substrate's absorption rate (approximate consumption of 0.10 - 0.15 kg/m² per coat) and the amount of product to be applied.
- It is recommended to cover with mortar, concrete, or plaster at least 30 minutes after applying the bonding agent, and at most after 48 hours.
- Prevent any dust from settling on the primer, as this will reduce its adhesion.
- Clean tools immediately after use, before the product hardens.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	Uso
Roller	0-10%
Air-less gun	Uso

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Project			
MAX	Montó Puente de Unión Tack		Mortero de obra: cemento, yeso, cal
STD			

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in fire. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 4 L, 12 L