

MONTO PUENTE DE UNIÓN GRIP



FAMILY LINE

PREPARACIONES, FONDOS E IMPR.
IMPRIMACIONES SUELOS

DESCRIPTION AND NATURE

Water-based, adhesive, textured primer. Bonding agent between mortars, specifically designed for non-absorbent construction surfaces. Can also be used on absorbent substrates.

USAGES

Floors and walls
Indoors/Outdoors
Marble
Ceramic
Non-absorbent supports
Stone
Undamaged rough mortar coats.
Plaster finishing
Cement, Plaster, Concrete, Brick
It enables the adhesion of leveling and rendering mortars to non-porous and/or polished substrates

PROPERTIES

- Low odour
- Excellent adhesion
- Good applicability
- Mortar bonding bridge
- Adhesion on a wide range of surfaces

TECHNICAL CHARACTERISTICS

Referencia Color	MONTO PUENTE DE UNIÓN GRIP
Finish	Rough
Specific weight	(1,78±0,03) kg/l
Viscosity	(350±30)PO
Solids in volume	66±1
Solids in weight	82±1
VOC	Cat. h/BA 50/30 (2007/2010):0,64 g/l
Aproximated performance by coat	2-3 m ² /Kg

Dry to touch	30min
Colours	Red
Classification	AFNOR: NFT. 36005 - Famille I. Classe 7b2

SURFACE PREPAIRING

New surfaces

- Clean the surface of any foreign matter and/or residue.
- The surface must be dry, clean, and free of dust, particles, oils, or any other particles that could impair the material's adhesion to the substrate.

Restoring and maintenance

This product is intended to be used as an intermediate layer and not as a finish, therefore no restoration or maintenance recommendations are included.

WAY OF USE

Application notes

- The product is supplied ready to use and can be diluted up to 10%.
- Apply the product with a brush or roller.
- Apply to clean, dry or slightly damp substrates, but never waterlogged.
- It is recommended to apply the product with a minimum of 0.3 kg/m² per coat to ensure proper adhesion.
- It is advisable to cover with mortar, concrete, or plaster at least 60 minutes after applying the bonding agent, and at most after 24-72 hours.
- Clean tools immediately after use before the product hardens.

Solvent for dilution and cleaning

Water

Way of use

Painting brush

Roller

Aproximate dilution

Uso

0-10%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Project			
MAX	Montó Puente de Unión Grip		Mortero de obra: cemento, yeso, cal
STD			

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

6 Kg, 20 Kg