



FAMILY ANTIHUMEDAD E IMPERMEABILIZAC.
LINE IMPERMEABILIZACION HORIZONTAL

DESCRIPTION AND NATURE

Single-component 100% polyurethane water-based aliphatic elastic membrane. For terraces and roofs. Waterproofing agent with excellent adhesion, forms a tenacious, seamless, waterproof, breathable, washable, hydrophobic coating that is stable at extreme temperatures. Mesh is essential for higher protection.

USAGES

Outdoor/Indoor
 Waterproofing of decks, terraces or roofs
 Fibre-cement
 Roofing tiles
 Geotextile
 Concrete
 Cement
 Brick
 Catalan tile
 Sprayed polyurethane
 Previously primed metal: iron, steel, galvanised metal, aluminium, copper, etc.
 Asphalt covering after priming

PROPERTIES

Capillary absorption and liquid water permeability: $w < 0.1 \text{ kg/m}^2 \cdot \text{h}^{0.5}$ according to UNE EN 1504-2; W3 (maximum impermeability) according to UNE EN 1062-1
 Classe Reaction classification to external fire: Broof (t1) according to UNE-EN 13501-1
 Excellent adhesion. Adhesion by pull-off test: 2.4 MPa (rigid systems with traffic loads $\geq 2.0 \text{ MPa}$ according to UNE EN 1504-2)
 100% waterproof hydrophobic membrane. Resistant to water logging (UNE-EN 1928)
 100% aliphatic polyurethane. High resistance to UV radiation. Does not yellow
 High flexibility and elasticity in extreme weather conditions. It forms a highly fracture resistant membrane on the substrate. Cracking resistance Class A5 (23°C, $> 2.5 \text{ mm}$) and Class A5 (-10°C, $> 2.5 \text{ mm}$) according to UNE EN 1062-1
 Determination of tensile properties according to UNE EN ISO 527-3: 196% elongation and 4 N/mm² tensile strength
 Solar Reflectance Index (SRI) = 104 [ASTM E1980-1]
 Tileable
 Passable for heavy or permanent pedestrian traffic (Category P4 according to EAD 030350-00-0402 (Liquid roof waterproofing systems). Adhesion after thermal compatibility according to UNE EN 1504-2 $> 2.0 \text{ MPa}$ for rigid systems under traffic loads
 The product can be guaranteed for up to 15 years on brick, Catalan tile or cement mortar. Consult conditions
 CE Marking. Complies with UNE EN 1504-2:2005, used for the surface protection of concrete, for the following uses: increase in resistivity by limiting moisture content, moisture control and protection against penetration
 Carbon dioxide permeability: $s_D > 50 \text{ m}$ in accordance with UNE EN 1504-2; C1 (anti-carbonation) in accordance with UNE-EN 1062-1
 Water vapour permeability: Class I in accordance with UNE EN 1504-2; V2 (highly breathable) in accordance with UNE-EN 1062-1



TECHNICAL CHARACTERISTICS

Referencia Color KORAZA MEMBRANA 100 PU BLANCO
 Finish Semi-matt

Fecha de Alta

19-12-2023

Versión

17 - 20/08/2026

Specific weight	1,27± 0,05 kg/l
Viscosity	130 +/- 10 PO
Solids in volume	42± 1
Solids in weight	56± 1
VOC	Cat. i/BA 140/140 (2007/2010):20,16 g/l
Aproximated performance by coat	1,5-2 m²/L

Dry to touch	(20°C HR:60%):4-6h
Dry to repaint	(20°C HR:60%):24h
Colours	White 102, Red 152, Grey 189

SURFACE PREPAIRING

New surfaces

Cement mortar:

1. Wait until fully set (at least 30 days).
2. Clean the surface of any foreign substances, residues and poorly adhered product. Treat mouldy substrates with Monto Limpia Moho.
3. Use abrasive blasting to prevent efflorescence and neutralise alkaline surfaces. On very smooth surfaces, key lightly with sandpaper. Putty with Plasmont Fibra Elástico if necessary.
4. The substrate must be completely dry before preparation. The humidity value measured with a hygrometer must be less than 4%.
5. Apply Fijamont or Epoxy Primer Floors over the entire cement mortar surface to completely seal the substrate.

Catalan tile or matt porous brick:

1. Same as on cement mortars, without the need to apply Fijamont.

Roofing felt, polyurethane foam:

1. Same as on cement mortars, without the need to apply Fijamont, check adhesion. Anchor with Epoxy Primer Floors.

Ferrous and non-ferrous metal surfaces such as galvanised metals or aluminium:

1. Clean the surface of any foreign substances, residues and poorly adhered product.
2. Apply Montoprimer Total Acqua as a primer to ensure adhesion.

Restoring and maintenance

1. Completely remove poor-condition or loose old paint.
2. Gloss surfaces should be keyed to ensure good adhesion.
3. On painted surfaces, check that the paint is solid and has good adhesion. Determine the composition of existing paint and check for incompatibilities with the product. Remove all dust and dirt before repainting. If it is not solid, remove to new surface underneath.
4. Before preparing the surface, it must be completely dry, the humidity value measured with a hygrometer should never be higher than 4%.
5. Properly putty the defects in the substrate.
6. On mouldy substrates, pre-treat with Monto Limpia Moho.
7. For maintenance on already waterproofed surfaces, two coats of 0.35 l/m2 are recommended.

WAY OF USE

Application notes

GENERAL CONSIDERATIONS:

- Shake the product until evenly mixed.
- Do not apply the product at temperatures below 5°C or above 35°C.
- Do not apply with risk of imminent rain or in humid environments.
- The substrate must be completely dry.
- The substrate temperature must be above 5°C to avoid freezing and below 40°C to avoid defects in the application.
- For maximum performance it is recommended not to dilute the product. Ready to use.

Minimum recommended consumption (allow to dry for 24 hours between coats):

1. 1st coat of 0.5 L/m2.
2. Incorporate fibreglass mesh (wet, must be properly impregnated).
3. 2nd coat of 0.5 L/m2.
4. 3rd coat of 0.5 L/m2 (fibreglass mesh must be completely submerged).

For warranty coverage, it is necessary to apply 1.5 L/m² and install a fibreglass mesh (check conditions).

*Note on the mesh: To obtain the certificate, it is necessary to apply the mesh according to the above specifications, the required meshes being: FIBERGLASS FABRIC ROLL 1x50 M/L REGA MT (656700/10/1) or FIBERGLASS FABRIC ROLL 1x50 ML VISA MT (656700/10/2).

OTHER RECOMMENDATIONS:

It can be in frequent but not permanent contact with water (does not re-emulsify). Resists standing water and suitable for wet areas, but is not intended to be submerged or to protect against permanent accumulation of water. Not suitable for waterproofing water tanks or swimming pools. To ensure watertightness, the reinforcement of singular points and of the entire roof with fibreglass mesh is mandatory for greater mechanical resistance and durability.

In order to avoid stresses on the polyurethane membrane, it is necessary to reinforce active cracks, half-rounds and any other unique element with fibreglass mesh. It must be laid with the membrane fresh, before applying the continuous coating on the rest of the surface. Do not use on substrates with rising damp.

In indoor environments, provide good ventilation and air renewal. Drying times and film curing may vary depending on humidity and ventilation.

In case of tiling or use under screed: apply 2-3 coats with a total consumption of 1.5 L/m². Do not apply more than 0.5 mm per coat (0.6-0.7 L/m²). Reinforcement with fibreglass reinforcement mesh, respecting the drying time between coats. After the application of the last layer, silica aggregate shall be applied while the membrane is still wet, with a consumption of 0.5 to 1 kg/m² of medium-sized silica aggregate (approx. 350 microns) to ensure proper adhesion of the tiling. Wait at least 72 hours before covering with cement.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	0-5%
Roller	0-5%
Air-less gun	0-10%
Air-mix gun	0-10%
Aerographic gun	0-10%
Low pressure turbo	0-10%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Sprayed PUR foam			
MAX	Imprimación Epoxi Suelos	Koraza Membrana 100% PU + Malla de fibra de vidrio	Koraza Membrana 100% PU
STD	Imprimación Epoxi Suelos	Koraza Membrana 100% PU + Malla de fibra de vidrio	Koraza Membrana 100% PU
Metallic surfaces			
MAX	Montoprimer Total Acqua	Koraza Membrana 100% PU + Malla de fibra de vidrio	Koraza Membrana 100% PU
STD	Montoprimer Total Acqua	Koraza Membrana 100% PU + Malla de fibra de vidrio	Koraza Membrana 100% PU
Masonry mortar			
MAX	Imprimación Epoxi Suelos	Koraza Membrana 100% PU + Malla de fibra de vidrio	Koraza Membrana 100% PU
STD	Fijamont	Koraza Membrana 100% PU + Malla de fibra de vidrio	Koraza Membrana 100% PU
Old paintings			
MAX	Imprimación Epoxi Suelos	Koraza Membrana 100% PU + Malla de fibra de vidrio	Koraza Membrana 100% PU

Fecha de Alta

19-12-2023

Versión

17 - 20/08/2026

STD Koraza Membrana 100% PU + Malla
de fibra de vidrio

Koraza Membrana 100% PU

Asphalt fabric**MAX** Imprimación Epoxi SuelosKoraza Membrana 100% PU + Malla
de fibra de vidrio

Koraza Membrana 100% PU

STD Imprimación Epoxi SuelosKoraza Membrana 100% PU + Malla
de fibra de vidrio

Koraza Membrana 100% PU

Catalan plaque and Matte porous brick**MAX** Imprimación Epoxi SuelosKoraza Membrana 100% PU + Malla
de fibra de vidrio

Koraza Membrana 100% PU

STD Koraza Membrana 100% PU + Malla
de fibra de vidrio

Koraza Membrana 100% PU

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

4 L, 15 L