

# PLASMONT BRICOLAGE ESCAYOLA PLASTICA



**FAMILY** PREPARACIONES, FONDOS E IMPR.

**LINE** EN POLVO (MASILLAS)

## DESCRIPTION AND NATURE

Powder plaster of great hardness, withness and smooth finish. For small repairs of mouldings, manual works and mouldings. Quick setting.

## USAGES

Indoors  
Plaster finishing  
Manual Works

## PROPERTIES

- Whiteness
- Does not decrease
- Fast sanding
- Good adhesion
- fast hardening
- Very fine gross
- Very smooth finishes without sanding
- Drying fast
- Good applicability

## TECHNICAL CHARACTERISTICS

Referencia Color	PLASMONT BRICOLAGE ESCAYOLA PLASTICA
Finish	Matt
Specific weight	2,25± 0,05 kg/l
Solids in volume	100± 1
Solids in weight	100± 1
Aproximated performance by coat	Depending of product usage
Dry to touch	(20°C HR: 60%): Sanding: 4-6 h
Dry to repaint	(20°C HR: 60%): repainted 24 days
Colours	White

## SURFACE PREPARING

### New surfaces

Plaster and mortar cement:

- Test putty suitability on surface.
- Wait till complete drying of product (30 days minimum).
- Remove off any efflorescences and neutralize alkaline surfaces.
- Extremely polished surfaces should be treated to open pores.
- Remove off any foreing products or remains.
- Open any fissures or cracks until obtaining good condition surface. -Remove off any resulting dust by brushing and apply putty as indicated under Application Systems and Application points.
- Do not apply product in extremely thick layers.

-For extremely damaged surfaces, use suitable fixer (see family 6): Emulsion Fijadora, fijamont or Fijalite before applying putty.

### Restoring and maintenance

Remove off any remains or peeling of paint or any other foreign products. Open pore by sandpapering or any other mechanical systems.  
Test adherence level and treat as per new surfaces.

## WAY OF USE

### Application notes

- For its thinning, use only fresh, clean water.
- Use only indicated tools under "Application Systems", clean and rust-free.
- Surfaces should be anchored properly.
- Repaint only after indicated drying time, which depends on moistering and temperature conditions as well as layer thickness.
- Can be dried mechanically.
- Ovaldine, Montoplastica, Montoature, Esmalte Montosintetic, Luxatin and Select Decoration products are suitable for top coats.

### Solvent for dilution and cleaning

Way of use	Aproximate dilution
Stainless trowel	500ml de agua por kg de escayola
Pallette / spatula	500ml de agua por kg de escayola
Pallette	500ml de agua por kg de escayola

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>Project</b>			
<b>MAX</b>			
<b>STD</b>	Escayola plástica	Fijador	Familia 1, 4, 12

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

# PLASMONT BRICOLAGE ESCAYOLA PLASTICA

## PACKINGS

1 Kg



## FAMILY LINE

## DESCRIPTION AND NATURE

Powder plaster of great hardness, withness and smooth finish. For small repairs of mouldings, manual works and mouldings. Quick setting.

## USAGES

## PROPERTIES

- Whiteness
- Does not decrease
- Fast sanding
- Good adhesion
- fast hardening
- Very fine gross
- Very smooth finishes without sanding
- Drying fast
- Good applicability

## TECHNICAL CHARACTERISTICS

Referencia Color	
Finish	Matt
Specific weight	2,25± 0,05 kg/l
Solids in volume	100± 1
Solids in weight	100± 1
Aproximated performance by coat	Depending of product usage
Dry to touch	(20°C HR: 60%): Sanding: 4-6 h
Dry to repaint	(20°C HR: 60%): repainted 24 days
Colours	White

## SURFACE PREPARING

### New surfaces

Plaster and mortar cement:

- Test putty suitability on surface.
- Wait till complete drying of product (30 days minimum).
- Remove off any efflorescences and neutralize alkaline surfaces.
- Extremely polished surfaces should be treated to open pores.
- Remove off any foreing products or remains.
- Open any fissures or cracks until obtaining good condition surface. -Remove off any resulting dust by brushing and apply

Fecha de Alta

04-07-2007

Versión

3 - 14/06/2022

putty as indicated under Application Systems and Application points.

-Do not apply product in extremely thick layers.

-For extremely damaged surfaces, use suitable fixer (see family 6): Emulsion Fijadora, fijamont or Fijalite before applying putty.

### Restoring and maintenance

Remove off any remains or peeling of paint or any other foreign products. Open pore by sandpapering or any other mechanical systems.

Test adherence level and treat as per new surfaces.

## WAY OF USE

### Application notes

-For its thinning, use only fresh, clean water.

-Use only indicated tools under "Application Systems", clean and rust-free.

-Surfaces should be anchored properly.

-Repaint only after indicated drying time, which depends on moistering and temperature conditions as well as layer thickness.

-Can be dried mechanically.

-Ovaldine, Montoplastica, Montoature, Esmalte Montosintetic, Luxatin and Select Decoration products are suitable for top coats.

### Solvent for dilution and cleaning

#### Way of use

Stainless trowel

Pallette / spatula

Pallette

#### Aproximate dilution

500ml de agua por kg de escayola

500ml de agua por kg de escayola

500ml de agua por kg de escayola

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>Project</b>			
<b>MAX</b>			
<b>STD</b>	Escayola plástica	Fijador	Familia 1, 4, 12

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

202295


Fecha de Alta

04-07-2007

Versión

3 - 14/06/2022

# PLASMONT BRICOLAGE ESCAYOLA PLASTICA



## PACKINGS

1 Kg