

Fecha de Alta

18-04-2008

Versión

17 - 27/02/2020



FAMILY **TRATAMIENTOS DE LA MADERA / SISTEMAS TINTOMÉTRICOS**
LINE **PROTECTORES ALCIDICOS (P. A.)**

DESCRIPTION AND NATURE

Penetrating wood primer for maximum elasticity. With waterproof. Penetrating, not a film. Maximum protection if applied outdoors in color.

USAGES

Outdoors/Indoors

Wood

Environmental use: Only specialized staff

Use for general public

PROPERTIES

Elasticity

For maximum protection outdoors, give it coloured

Outdoor maximum protection if applied over Montoxyl Fondo Coloured

Sea side & high-mountain weather resistant

No cracking at all

Does not form blisters

Water steam transpirable

- Highlights the wood's natural grain

Penetration capacity

Good applicability

TECHNICAL CHARACTERISTICS

Referencia Color	MONTOXYL CLASSIC FONDO
Finish	Transparent
Specific weight	0,84± 0,05 kg/l
Viscosity	25 +/- 5 SG
Solids in volume	25± 1
Solids in weight	31± 1
VOC	Cat. e/BD 500/400 (2007/2010):400,00 g/l
Aproximated performance by coat	8-12 m ² /L
Dry to touch	(20°C HR: 60%): 1-2 h
Dry to repaint	(20°C HR: 60%): 1-2 h
Colours	Base: Transparent 901. Wood chart colors. Montomix, Cromiservice. Tintado with universal Montotinte, max 5%

SURFACE PREPAIRING

New surfaces

New wood:

1. The base must be free from foreign materials and/or waste matter.
2. Apply to wood with a moisture content of less than 20%.
3. Apply to wood which is healthy, dry and free from grease and dust.

Old wood

1. Sand down and remove any remnants of glue from the joints and defects from mechanical process.
2. If the wood shows signs of ageing it must first be sanded down and any dust removed using a plane or other mechanical device.
3. By using a paint gun; the most highly recommended is the Airless System

Fecha de Alta

18-04-2008

Versión

17 - 27/02/2020

Restoring and maintenance

Varnished or painted wood:

1. If the wood has been varnished using Montoxyl matt or satin type lasures, remove foreign materials, remove any varnish which is loose or in poor condition, gently sand down, remove the sanding dust and proceed as with new wood.
2. If the wood has been varnished using Montoxyl type flexible and penetrating protectors, remove foreign materials, remove any varnish which is loose or in poor condition, gently sand down, remove the sanding dust and proceed as with new wood.
3. If it has been varnished using a closed pore varnish like Barniz Sintético Universal Matt, Satin or Gloss, Barniz Velero, Barniz Alta Montaña o similar, strip down with Quitamont Universal or by mechanical means and proceed as with new wood if blisters or cracks have appeared or edges are raised. If the surface is in good condition, gently sand down, remove the sanding dust and proceed as with new wood.
4. If the wood has previously been varnished with cellulose or polyurethane varnishes, strip down using Quitamont Universal (Code: 3510) or by mechanical means and proceed as with new wood.
5. If the wood has been enamelled with a synthetic enamel such as Montosintetic, Marisma, Luxatín or similar, strip down with Quitamont Universal or by mechanical means and proceed as with new wood.

WAY OF USE

Application Notes

Stir the product until perfectly blended.

Apply thin, even layers.

Do not apply the product at high temperatures or on surfaces exposed to strong insolation.

Ensure good ventilation while product is drying.

Do not apply with relative moisture over 80%.

Solvent for dilution and cleaning

1401, 1402, Símil Aguarrás

Way of use	Aproximate dilution
Painting brush	Uso
Roller	Uso
Air-less gun	Uso
Air-mix gun	Uso
Aerographic gun	Uso
Low pressure turbo	Uso
Immersion	Uso

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
New /old wood indoor/outdoor			
MAX	Al exterior: Anticarcomas Klearxyl Di	Montoxyl classic fondo Color	Montoxyl classic fondo Color
STD	Al exterior: Anticarcomas Klearxyl Di		Montoxyl classic fondo Color
Open pore varnished wood			
MAX	Al exterior: Decapar+ Anticarcomas Klearxyl Di	Montoxyl classic fondo Color	Montoxyl classic fondo Color
STD	Al exterior: Decapar + Anticarcomas Klearxyl Di		Montoxyl classic fondo Color
Closed pore wood			
MAX	Al exterior: Anticarcomas Klearxyl Di	Montoxyl classic fondo Color	Montoxyl classic fondo Color
STD	Al exterior: Anticarcomas Klearxyl Di		Montoxyl classic fondo Color

SECURITY

Fecha de Alta

18-04-2008

Versión

17 - 27/02/2020

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 5 L