

MONTOXYL LASURE ACQUA SATINADO



FAMILY TRATAMIENTOS DE LA MADERA / SISTEMAS TINTOMÉTRICOS
LINE PROTECTORES AL AGUA (P. A.)

DESCRIPTION AND NATURE

Transparent lasure for protect interior and exterior wood, with UV protectors.

USAGES

Outdoors/Indoors

For maximum protection, finish in colour.

Recommended previously created with primer

Specially recommended for mountain and coastal areas

PROPERTIES

Penetration power

Provides open pore finish

- Do not apply white media, you can amarillarlos slightly, but does not alter the properties of the product.

Does not turn yellow

no need of sanding, but easy to do once dried

recommended number of coats : 2-3 coats over new wood, 1-2 coats as maintenance

No cracking at all

Does not form blisters

Water steam transpirable

Odourless when dry

- Endures brusque changes in the weather

- Flexible

- Microporous

- Highlights the wood's natural grain

- U.V. resistant

- May be used as a base when diluted, thus nourishing the wood

TECHNICAL CHARACTERISTICS

Referencia Color	MONTOXYL LASURE ACQUA SATINADO
Finish	Satin
Specific weight	0,98± 0,05 kg/l
Viscosity	8 +/- 2 PO
Solids in volume	20± 1
Solids in weight	22± 1
VOC	Cat. e/BA 150/130 (2007/2010): 130,00 g/l
Aproximated performance by coat	10-16 m ² /L
Dry to touch	(20°C HR: 60%): 2-4 h. Total: 12-24 h
Dry to repaint	(20°C HR: 60%): 12-24 h
Colours	Base: TR 900 Cromiservice and Montomix (max 5%) systems. Montotinte universal or water (max: 5%) Cumple con la NORMA UNE 23727-90 1ª R / REACTION FEU M1

SURFACE PREPAIRING

New surfaces

New wood

- 1.- On the outside, protect the wood with Klearxyl Di Anticarcomas from the attack of fungi and xylophagous insects.
- 2.- Surface should be free of any foreign products or remains.
- 3.- Apply on wood with less than 20% moisture content.
- 4.- Apply on wood in good condition, dry and free of grease and dust.
- 5.- Sandpaper and eliminate any remains in joints and mechanical faults.
- 6.- Old wood should be previously sanded and dust-free.

Restoring and maintenance

Painted or varnished surfaces:

- If they have been varnished with Barniz Lasure Acqua or Montoxyl Color, remove off foreign remains, or areas in bad condition, sandpaper slightly, brush any resulting dust and proceed as per new wood.
- If they have been varnished with close pore varnishes or similar apply a stripping product or use a mechanical system if any blisters or cracks have arisen and proceed as per new wood. If surfaces are in good condition, sandpaper slightly, brush any resulting dust and proceed as per new wood.
- If they have been varnished with cellulose or polyetherane based varnished, apply a stripping product or use a mechanical system and proceed as per new wood.
- If they have been painted with synthetic enamels apply a stripping product or use a mechanical system and proceed as per new wood.
- On the outside, protect the wood with Klearxyl Di Anticarcomas from the attack of fungi and xylophagous insects.
- In pieces already varnished with MONTOXYL LASURE ACQUA SATINADO and in order to maintain all its protective efficiency, it is advisable to periodically check the state / appearance of the surfaces. If deterioration is observed, due to impacts and / or scratches, etc. We recommend to clean and sand the damaged area and restore with MONTOXYL LASURE ACQUA MATE.

WAY OF USE

Application Notes

- Stir product completely.
- Only apply on clean and dry surfaces.
- Dilute product according to application system recommendations.
- Surface should be sanded previously to ensure good product penetration and wood levelling.
- For the first coat, it is recommended to prime with Fondo Lasure Acqua.
- Do not apply at high temperatures or on overheated surfaces exposed to sunshine.
- Keep room well ventilated while product is drying.
- Do not apply when moisture content is over 80%.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	fondo: 10-30%
Roller	10-30%
Air-less gun	30-50%
Air-mix gun	30-50%
Aerographic gun	10-30%
Low pressure turbo	10-30%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
varnished or painted wood			
MAX	Outdoor: Stripping+ Anticarcomas Klearxyl Di	Montoxyl Fondo Color	Lasure Acqua Satinado Color
STD	Outdoor: Stripping + Anticarcomas Klearxyl Di		Lasure Acqua Satinado Color
New wood/old outdoor			
MAX	Anticarcomas Klearxyl Di	Montoxyl Fondo Color	Lasure Acqua Satinado Color

MONTOXYL LASURE ACQUA SATINADO



STD Anticarcomas Klearxyl Di

Lasure Acqua Satinado Color

Old/New interior Wood

MAX Lasure Acqua o Montoxyl Fondo

Montoxyl Fondo

Lasure Acqua Satinado

STD Lasure Acqua o Montoxyl Fondo

Lasure Acqua Satinado

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 4 L