

BARNIZ PARQUET ACQUA BRILLO



FAMILY TRATAMIENTOS DE LA MADERA / SISTEMAS TINTOMÉTRICOS
LINE POLIURETANOS AL AGUA (SUELOS)

DESCRIPTION AND NATURE

Transparent gloss water-based polyurethane varnish for varnishing woods in interiors when a good rub resistance and resistance to detergents is desired.

USAGES

Indoors
Parquet
Wood

PROPERTIES

Strongness
Transparence
Colourless
Good adhesion
Washability
useful like primer and finish
finishes with strong filling capability
colors as per wood chart with Montomix System
- Water-based
Odourless when dry

TECHNICAL CHARACTERISTICS

Referencia Color	BARNIZ PARQUET ACQUA BRILLO
Finish	Gloss
Specific weight	1,01± 0,05 kg/l
Viscosity	50 +/- 5 SG
Solids in volume	27 ± 1
Solids in weight	29± 1
VOC	Cat. e/BA 150/130 (2007/2010): 130,00 g/l
Aproximated performance by coat	12-16 m ² /L
Dry to touch	(20°C HR: 60%): 1-2 h
Dry to repaint	(20°C HR: 60%): 12-24h . Total 3 días
Colours	Base: Transparent

SURFACE PREPAIRING

New surfaces

New woods.

The surface must be free from foreign products and/or residues.

Apply to wood with a moisture content of less than 20%.

Apply to healthy, grease-free, dust-free and dry wood.

Sand and remove any remnants of glue from the joints and faults from machining.

If the wood shows signs of ageing it must first be sanded down and any dust removed using a plane or other mechanical device.

Restoring and maintenance

New woods.

The surface must be free from foreign products and/or residues.

BARNIZ PARQUET ACQUA BRILLO

Apply to wood with a moisture content of less than 20%.

Apply to healthy, grease-free, dust-free and dry wood.

Sand and remove any remnants of glue from the joints and faults from machining.

If the wood shows signs of ageing it must first be sanded down and any dust removed using a plane or other mechanical device.

Varnished or painted woods:

- If the wood has been varnished with Montoxyl colour (code 1300): remove foreign products, remove any loose or peeling varnish, lightly sand, remove dust from sanding and proceed as on new woods.

- If the wood has been varnished with closed pore varnishes such as Barniz Sintético Universal Mate (code 1350), Satinado (code 1360), Brillante (code 1370) Barniz Veleró (code 1380), Barniz Alta Montaña (code 1385) or similar, remove by stripping with Quitamont Universal (code 3510) or by mechanical means, and proceed as on new woods.

- If the wood has been varnished with cellulose or polyurethane varnishes, remove by stripping with Quitamont Universal (code 3510) or by mechanical means, and proceed as on new woods.

- If the wood has been enamelled with synthetic enamel (Montosintético (code 2020, code 2024), Marisma (code 2010, code 2014), Luxatín (code 2028) or similar), remove by stripping with Quitamont Universal (code 3510) or by mechanical means, and proceed as on new woods.

Stir the product until perfectly blended.

Apply on clean and dry substrates.

Apply following the recommended dilutions as described in the Application Systems section.

Sand before application to ensure good penetration and smoothing on the wood.

Do not apply the product at high temperatures or on surfaces exposed to strong sunlight.

Ensure good ventilation while product is drying.

Do not apply with relative humidity over 80%.

WAY OF USE

Application Notes

Stir the product until perfectly blended.

Apply on clean and dry substrates.

Apply following the recommended dilutions as described in the Application Systems section.

Sand before application to ensure good penetration and smoothing on the wood.

Do not apply the product at high temperatures or on surfaces exposed to strong sunlight.

Ensure good ventilation while product is drying.

Do not apply with relative humidity over 80%.

Solvent for dilution and cleaning

Water

Way of use

Painting brush

Roller

Air-less gun

Air-mix gun

Aerographic gun

Low pressure turbo

Aproximate dilution

FONDO: 10-20%. ACABADO: 0-5%

FONDO: 10-20%. ACABADO: 0-5%

FONDO: 10-20%. ACABADO: 0-5%

FONDO: 10-20%. ACABADO: 0-5%

FONDO: 10-20%. ACABADO: 0-5%

FONDO: 10-20%. ACABADO: 0-5%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Painted or varnished wood (closed pore) indoor			
MAX	decapar+Barniz Parquet Poliuretano al Agua Brillo	Barniz Parquet Poliuretano al Agua Brillo	Barniz Parquet Poliuretano al Agua Brillo
STD	decapar+Barniz Parquet Poliuretano al Agua Brillo	Barniz Parquet Poliuretano al Agua Brillo	Barniz Parquet Poliuretano al Agua Brillo
Wood			

BARNIZ PARQUET ACQUA BRILLO

MAX	Montoxyl fondo	Barniz Parquet Poliuretano al Agua Brillo	Barniz Parquet Poliuretano al Agua Brillo
STD	Barniz Parquet Poliuretano al Agua Brillo	Barniz Parquet Poliuretano al Agua Brillo	Barniz Parquet Poliuretano al Agua Brillo

Open pore varnished wood

MAX	Barniz Parquet Poliuretano al Agua Brillo	Barniz Parquet Poliuretano al Agua Brillo	Barniz Parquet Poliuretano al Agua Brillo
STD	Barniz Parquet Poliuretano al Agua Brillo	Barniz Parquet Poliuretano al Agua Brillo	Barniz Parquet Poliuretano al Agua Brillo

Ground

MAX	Barniz Parquet Poliuretano al Agua Brillo	Barniz Parquet Poliuretano al Agua Brillo	Barniz Parquet Poliuretano al Agua Brillo
STD	Barniz Parquet Poliuretano al Agua Brillo	Barniz Parquet Poliuretano al Agua Brillo	Barniz Parquet Poliuretano al Agua Brillo

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 4 L