

# MONTOLAC SATINADA BLANCA CM-70



**FAMILY**      **TRATAMIENTOS DE LA MADERA / SISTEMAS TINTOMÉTRICOS**  
**LINE**            **LACAS NITRO PIGMENTADAS**

## DESCRIPTION AND NATURE

Nitrocellulose lacquer satin finish, white, fast drying high solids content for use in interiors.

## USAGES

Indoors

Wood

Product for exclusive use in industries regulated by Directive 2010/75 Chapter V.

## PROPERTIES

- Drying fast
- Good hiding power capacity

## TECHNICAL CHARACTERISTICS

Referencia Color	MONTOLAC SATINADA BLANCA CM-70
Specific weight	1,07± 0,05 kg/l
Viscosity	105 +/- 30 SG
Solids in volume	27± 1
Solids in weight	42± 1
Aproximated performance by coat	Depending of product usage

## SURFACE PREPAIRING

### New surfaces

New wood:

- The base must be free from foreign materials and/or waste matter.
- Prime with the right products.
- Apply to wood with a moisture content of less than 12%.
- Apply to healthy wood that is dry and free from grease and dust.
- Sand down and remove any remains of glue in joints and defects from mechanical processes.
- If the wood shows signs of aging must be pre-sanded and removing dust by brushing or other mechanical means.

### Restoring and maintenance

-Varnished or painted wood:

- If the wood has been varnished with varnishes or paints that have been diluted with white spirit, turpentine, imitation turpentine or solvents for synthetics and oils, these must be removed using a universal stripper or by employing mechanical means, until the new wood is reached.
- If in doubt remove the varnish, lacquer or enamel above.
- If applied on nitrocellulose varnish or polyurethane sand to open the pore, remove the resulting dust with a brush and re-varnish.
- In any case, check the adhesion on the previous varnish, and in case of doubt, remove it.
- If silicone-based domestic cleaning products have been used for maintenance, it is advisable to sand the wood until they have been completely removed.

## WAY OF USE

### Application notes

- Stir the products until perfectly blended.
- Properly dilute the first coat to get a good leveling.
- They should never be applied thicknesses exceed the corresponding to 12-14m<sup>2</sup> / l as described in Section Performance.
- Do not apply the product at high temperatures nor to surfaces exposed to strong insolation.
- Ensure good ventilation while product is drying.
- Do not apply in relative humidity of over 75-80%. Excessive moisture can cause "whitenings".
- Respect the minimum time between coats in order to prevent mixing.
- This Product can be re-varnishing with synthetic varnishes.
- The base must be free from foreign materials and/or waste matter.
- Apply to wood with a moisture content of less than 12%.
- Apply to healthy wood that is dry and free from grease and dust.
- Sand down and remove any remains of glue in joints and defects from mechanical processes.
- If the wood shows signs of aging must be pre-sanded and removing dust by brushing or other mechanical means.

### Solvent for dilution and cleaning

Way of use                      Aproximate dilution

## SYSTEM

### Procedures depending of surface type

Primer

Intermedium

Finish

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Product of exclusive use for premises regulated under RD 117/2003 or 1999/13/CE regulations

## NOTE

Maximum recommended storage time : 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

## PACKINGS

5 L, 25 L