

Fecha de Alta

09-07-2007

Versión

4 - 04/03/2016


**FAMILY** PREPARACIONES, FONDOS E IMPR.

**LINE** PASIVANTE

**DESCRIPTION AND NATURE**

Rust neutralizer which through a chemical reaction converts the rust into a perfectly adherent and passive film.

**USAGES**

Outdoors/Indoors

Iron or oxidized steel

Replaces mechanical treatment, prior to antioxidant primer.

**PROPERTIES**

Applicability

Penetration power

Fast drying

No sanding necessary for repainting. Non expensive maintenance

Penetration power

to fix fragile rusting on the support

temporary anti-rust effect

**TECHNICAL CHARACTERISTICS**

Referencia Color	OXIFIN
Finish	Metallic finish
Specific weight	0,98± 0,05 kg/l
Solids in volume	13± 1
Solids in weight	13± 1
Aproximated performance by coat	20 m <sup>2</sup> /L
Dry to touch	(20°C HR: 60%): 3h
Dry to repaint	(20°C HR: 60%): mín 3 h. Máx: 48 h
Colours	Bluish Black

**SURFACE PREPAIRING**
**New surfaces**

- New metal surfaces:
- Apply to clean, dry surfaces free from grease and dust.
- Remove rust with a brush.

**Restoring and maintenance**

- Enamelled iron and its derivatives:
- For the best adhesion and anti-corrosive results, we recommend removing traces of old paint.
- Follow the instructions for new surfaces for removing other products, degreasing, cleaning and treating rust.

**WAY OF USE**
**Application Notes**

- Stir the product until perfectly homogenised.
- Apply to clean, dry substrates, removing dirt with degreasing agents or detergents and clean water.
- Apply according to the instructions in the attached application table.
- Do not apply the product at high temperatures or on surfaces exposed to strong sunlight.

Fecha de Alta

09-07-2007

Versión

4 - 04/03/2016

- Ensure the area is well ventilated while the product is drying.
- Do not apply with relative humidity of over 80%.

### Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	Al uso
Roller	Al uso

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>Iron, Steel</b>			
<b>MAX</b>			
<b>STD</b>	IXIFIN	IMPRIEPOX M10, IMPRIPOL, MINIO DE PLOMO, ANTIOXIDANTE BLANCA	MONTOSINTETIC, LUXATIN, MARISMA, FERRUM, MONTOACRILIC, MONTONATURE, ACRIPOL

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

## PACKINGS

0.125 L, 0.25 L, 1 L, 4 L