

Fecha de Alta

27-01-2009

Versión

15 - 21/07/2020



FAMILY ESMALTES
LINE SINTETICOS (1 COMPONENTE)

DESCRIPTION AND NATURE

Pigmented gloss glycerophthalic synthetic enamel, recommended in alkyd systems on steel, wood and plasterwork.

USAGES

Outdoors/Indoors

Iron

In order to apply on galvanized iron to consult with the technical department

PROPERTIES

- Makes a film
- Penetration power
- Strong resistance to the atmospherical factors
- With micronic pigments wich are UV protectives
- No cracking at all
- Does not form blisters
- Odourless when dry
- Good applicability

TECHNICAL CHARACTERISTICS

Referencia Color	MARISMA BRILLANTE BLANCO
Finish	Gloss
Specific weight	1,12± 0,05 kg/l
Viscosity	75 +/- 5 KU
Solids in volume	29± 1
Solids in weight	50± 1
VOC	Cat. d/BD 400/300 (2007/2010):274,09 g/l
Aproximated performance by coat	12-14 m ² /L
Dry to touch	(20°C HR:60%): 2-4 h
Dry to repaint	(20°C HR:60%): 24 h
Colours	White, other colours from the Marisma chart, industrial applications chart: Zona Azul 184, Rojo 152, Verde 128. RAL group A, B and C card colors.

SURFACE PREPAIRING

New surfaces

New wood surfaces:

1. The base must be free from foreign materials and/or waste products.
2. Apply on wood with a moisture content of less than 20%.
3. Apply on healthy wood that is dry and free of grease and dust.
4. Sand down and remove any remains of glue in joints and defects from mechanical processes.
5. If the wood shows signs of ageing it must first be sanded down, primed and any dust removed by brushing or any other mechanical device.
6. In this instance the most suitable primer is Selladora Sellalux.

Iron and derivatives:

1. To protect the surface, prior to decoration work, treat with suitable primers (family 6) following the specifications given on

Fecha de Alta

27-01-2009

Versión

15 - 21/07/2020

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.375 L, 0.75 L, 4 L, 15 L