

MONTOSPORT PISCINAS POSEIDON STD CLO.



FAMILY IMPERMEAB. Y REVEST. FACHADAS / SISTEMAS TINTOMÉTRIC
LINE REVESTIMIENTOS LISOS

DESCRIPTION AND NATURE

Semi-matt paint for concrete swimming pools, with chlorinated rubber, with very good resistance to chemical agents, alkalinity and moisture.

USAGES

Outdoors/Indoors

Cement

Metal

Applicable on the habitual materials in construction: mortars, encofrados, cement

PROPERTIES

Adherence

Surface leveling

High performance

Fast drying

Water resistant

Alacalynity resistance

The product may become discoloured depending on the type and concentration of the disinfectant used.

Strong resistance to the atmospherical factors

TECHNICAL CHARACTERISTICS

Referencia Color MONTOSPORT PISC. POSEIDON STD CLO. AZUL

Finish Semi-matt

Specific weight 1,35± 0,05 kg/l

Viscosity 80 +/- 10 KU

Solids in volume 37± 1

Solids in weight 61± 1

Aproximated performance by coat 6-8 m²/L

Dry to touch (20° C RH: 60%): 5-20 min. Swimming pool filling 8 days

Dry to repaint (20° C HR: 60%): 24 h

Colours Blue 183 White 102

SURFACE PREPAIRING

New surfaces

Cement mortar: - Wait until completely set (minimum 30 days).

-Use an abrasive jet to remove any potential efflorescence from the base and neutralise alkaline surfaces.

-Sand down highly polished surfaces to open up the mortar.

-Remove any foreign products and/or residues from the base.

-Use outdoor plaster to fill any defects in the base (in PREPARING BASES family, see lines corresponding to powder plaster and prepared fillers to select a suitable solution).

-Treat mouldy bases with Montolimp.

Restoring and maintenance

Fully remove any old paint that is loose or in bad condition.

Dull down glossy surfaces to ensure good adhesion.

On painted bases, check the solidity and anchorage of the paint and the paint type in order to avoid potential incompatibilities. Remove dust and dirt before repainting. It is recommended that you do not apply it over water-based

Fecha de Alta

14-11-2008

Versión

1C - 13/06/2019

swimming pool paint

-Use outdoor plaster to fill any defects in the base (in PREPARING BASES family, see lines corresponding to powder plaster and prepared fillers to select a suitable solution).

Walls with mould should first be treated with Montolimp.

WAY OF USE

Application Notes

Apply on well-dried bases.

You must check the adhesion of the paint to old paint between coats, as it is common to repaint swimming pools regularly, meaning that the adhesion between coats can be greater than the adhesion of the old paint to the base, causing chipping of layers of paint that are weakly adhered.

Should you treat the surface with hydrochloric acid to open the pore, clean with plenty of water and leave to dry.

Dilute the product according to the porosity and state of the base.

This product is resistant to chlorine and chlorine derivatives if concentration is within the limits indicated in RD 742/2013, 27th of September.

For any other treatment (flocculants, algacides ...), check with the supplier the possibility to be used in painted pools.

Solvent for dilution and cleaning

Solvent 1403

Way of use	Aproximate dilution
Painting brush	5-10%
Roller	5-10%
Air-less gun	10-20%
Air-mix gun	10-20%
Aerographic gun	10-20%
Low pressure turbo	5-10%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Old paintings in bad state			
MAX			
STD	Eliminar + Montosport Pisc. Clorocaucho Diluido		Montosport Pisc. Clorocaucho
Old painting in good state			
MAX			
STD	Montosport Pisc. Clorocaucho Diluido		Montosport Pisc. Clorocaucho
Wood			
MAX		Montosport Pisc. Clorocaucho Diluido	
STD			Montosport Pisc. Clorocaucho Diluido
Cement			
MAX	Fijamont	Montosport Pisc. Clorocaucho Diluido	
STD	Montosport Pisc. Clorocaucho Diluido		Montosport Pisc. Clorocaucho
Support weak			
MAX	Fijamont	Montosport Pisc. Clorocaucho Diluido	
STD	Montosport Pisc. Clorocaucho Diluido		Montosport Pisc. Clorocaucho
Plaster			
MAX		Montosport Pisc. Clorocaucho Diluido	

MONTOSPORT PISCINAS POSEIDON STD CLO.

STD

Montosport Pisc. Clorocaucho Diluido

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

4 L, 15 L