

# PLASMONT AL USO REPARACION RAPIDO



**FAMILY** PREPARACIONES, FONDOS E IMPR.

**LINE** AL USO (MASILLAS)

## DESCRIPTION AND NATURE

Light acrylic filler. Ideal for quick repairs to cracks, holes, etc.  
0% shrinkage, very thick consistency and high filling capacity.

## USAGES

Outdoor/Indoor

Plaster

Cement

Concrete

Brick

Brick

Cement mortars

Plaster

Wood

## PROPERTIES

Acoustic insulator

Thermal insulator

Low thermal conductivity

Energy saving

Anticondensation

Fast drying

Outdoor resistance

- Easy to sand

Does not fall off base

Thermal conductivity of the insulating micro-bubbles: 0.057 W/mk

## TECHNICAL CHARACTERISTICS

Referencia Color PLASMONT AL USO REPARACION RAPIDO

Finish Matt

Specific weight 0,54± 0,05 kg/l

Solids in volume 65± 1

Solids in weight 45± 1

Minimum recommended thickness Ilimitado

Aproximated performance by coat Depending of product usage

Dry to touch (20°C HR:60%): 1 hour

Dry to repaint (20°C HR:60%): 1-4 hours / Depending on the minimum thickness

Colours White 103

## SURFACE PREPAIRING

### New surfaces

Cement/plaster mortar:

Check the suitability of the filler for the base.

Wait until fully hardened (at least 30 days)

Clean any efflorescence off the base, and neutralise alkaline surfaces.

On extremely smooth surfaces, sand lightly for tooth.

Clean any foreign products and/or residue from the base.

# PLASMONT AL USO REPARACION RAPIDO

Open up any cracks or fissures until you reach a sound base, brush off the dust, and apply the filler or plaster as shown in the sections Application Systems and Application.

- Do not apply thicker coats than the recommended maximum.

- On extremely crumbly surfaces, before applying the filler, fix it with the appropriate fixative: Emulsión Fijadora, Fijamont, Primer Montolite.

## Restoring and maintenance

Remove products from the base which are flaking or in poor condition, and raise a tooth on smooth surfaces by sanding or other mechanical means.

Check the adhesion and treat as for new BASES.

## WAY OF USE

### Application Notes

Using the tools shown in the application system, clean and free of rust.

Apply enough for the first coat.

It is possible to increase the number of coats to 3 or more to obtain a thicker layer, up to 15 mm .

Repaint after the indicated drying time. As this depends on humidity, temperature and the thickness of the applied product, when the product no longer clogs up sandpaper, this will mean it is ready to paint.

Suitable finishing products: Ovaldine, Montoplástica, Montonature, Esmalte Montosintético, Luxatín and Alta Decoración products.

### Solvent for dilution and cleaning

Water

#### Way of use

#### Aproximate dilution

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>New work</b>			
<b>MAX</b>	Emulsión Fijadora, Fijamont	Plasmont Al Uso Rápido	Pintura Plástica Montó
<b>STD</b>	Plasmont Al Uso Rápido		Pintura Plástica Montó
<b>Wood</b>			
<b>MAX</b>	Selladora	Plasmont Al Uso Rápido	Pintura Plástica Montó
<b>STD</b>		Plasmont Al Uso Rápido	Pintura Plástica Montó
<b>Support weak</b>			
<b>MAX</b>	Emulsión Fijadora, Fijamont	Plasmont Al Uso Rápido	Pintura Plástica Montó
<b>STD</b>	Plasmont Al Uso Rápido		Pintura Plástica Montó
<b>Old painting in good state</b>			
<b>MAX</b>	Plasmont Al Uso Rápido	Plasmont Al Uso Rápido	Pintura Plástica Montó
<b>STD</b>		Plasmont Al Uso Rápido	Pintura Plástica Montó
<b>Old paintings in bad state</b>			
<b>MAX</b>	Eliminar + Fijador	Plasmont Al Uso Rápido	Pintura Plástica Montó
<b>STD</b>	Eliminar	Plasmont Al Uso Rápido	Pintura Plástica Montó

## SECURITY

# PLASMONT AL USO REPARACION RAPIDO

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

Maximum recommended storage time : 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

## PACKINGS

0.75 L, 4 L



**FAMILY  
LINE**

## DESCRIPTION AND NATURE

Light acrylic filler. Ideal for quick repairs to cracks, holes, etc. 0% shrinkage, very thick consistency and high filling capacity.

## USAGES

## PROPERTIES

Acoustic insulator  
Thermical insulator  
Low thermal conductivity  
Energy saving  
Anticondensation  
Fast drying  
Outdoor resistance  
- Easy to sand  
Does not fall off base  
Thermal conductivity of the insulating micro-bubbles: 0.057 W/mk

## TECHNICAL CHARACTERISTICS

Referencia Color

Finish	Matt
Specific weight	0,54± 0,05 kg/l
Solids in volume	65± 1
Solids in weight	45± 1
Minimum recommended thickness	Ilimitado

# PLASMONT AL USO REPARACION RAPIDO

Fecha de Alta

19-05-2014

Versión

4 - 02/02/2018

Aproximated performance by coat      Depending of product usage

Dry to touch      (20°C HR: 60%): 1 hour

Dry to repaint      (20°C HR: 60%): 1-4 hours / Depending on the minimum thickness

Colours      White 103

## SURFACE PREPARING

### New surfaces

Cement/plaster mortar:

Check the suitability of the filler for the base.

Wait until fully hardened (at least 30 days)

Clean any efflorescence off the base, and neutralise alkaline surfaces.

On extremely smooth surfaces, sand lightly for tooth.

Clean any foreign products and/or residue from the base.

Open up any cracks or fissures until you reach a sound base, brush off the dust, and apply the filler or plaster as shown in the sections Application Systems and Application.

- Do not apply thicker coats than the recommended maximum.

- On extremely crumbly surfaces, before applying the filler, fix it with the appropriate fixative: Emulsión Fijadora, Fijamont, Primer Montolite.

### Restoring and maintenance

Remove products from the base which are flaking or in poor condition, and raise a tooth on smooth surfaces by sanding or other mechanical means.

Check the adhesion and treat as for new BASES.

## WAY OF USE

### Application Notes

Using the tools shown in the application system, clean and free of rust.

Apply enough for the first coat.

It is possible to increase the number of coats to 3 or more to obtain a thicker layer, up to 15 mm .

Repaint after the indicated drying time. As this depends on humidity, temperature and the thickness of the applied product, when the product no longer clogs up sandpaper, this will mean it is ready to paint.

Suitable finishing products: Ovaldine, Montoplástica, Montonature, Esmalte Montosintético, Luxatín and Alta Decoración products.

### Solvent for dilution and cleaning

Water


**Way of use      Aproximate dilution**

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>New work</b>			
<b>MAX</b>	Emulsión Fijadora, Fijamont	Plasmont Al Uso Rápido	Pintura Plástica Montó
<b>STD</b>	Plasmont Al Uso Rápido		Pintura Plástica Montó
<b>Wood</b>			
<b>MAX</b>	Selladora	Plasmont Al Uso Rápido	Pintura Plástica Montó
<b>STD</b>		Plasmont Al Uso Rápido	Pintura Plástica Montó
<b>Support weak</b>			
<b>MAX</b>	Emulsión Fijadora, Fijamont	Plasmont Al Uso Rápido	Pintura Plástica Montó

# PLASMONT AL USO REPARACION RAPIDO



**STD** Plasmont Al Uso Rápido

Pintura Plástica Montó

## Old painting in good state

**MAX** Plasmont Al Uso Rápido

Plasmont Al Uso Rápido

Pintura Plástica Montó

**STD**

Plasmont Al Uso Rápido

Pintura Plástica Montó

## Old paintings in bad state

**MAX** Eliminar + Fijador

Plasmont Al Uso Rápido

Pintura Plástica Montó

**STD** Eliminar

Plasmont Al Uso Rápido

Pintura Plástica Montó

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

## PACKINGS

0.75 L, 4 L