

Fecha de Alta

06-03-2008

Versión

5 - 03/03/2016

**FAMILY** PREPARACIONES, FONDOS E IMPR.**LINE** HIERRO Y METALES (MASILLAS)**DESCRIPTION AND NATURE**

Paste putty of two components, body type, with excellent anchorage on iron and metals, designed to cover defects and to equal surfaces before the painted one

USAGES

Outdoors/Indoors

Iron

Galvanized iron

Polyester

Cement mortars

PROPERTIES

Elasticity

Levelling

Thixotropic

Fast drying

Base putty

Fast sanding

High filling power, given its high solids content.

Good adhesion

- Easy to sand

Drying fast

No cracking at all

Good adhesion

TECHNICAL CHARACTERISTICS

Referencia Color	PLASMONT METALES CREMA
Mixture relation	100 partes (masilla): 2-2.5 (Catalizador Masilla)
Finish	Matt
Aproximated performance by coat	Depending of product usage
Dry to touch	(20°C HR: 60%): 5-10 min
Dry to repaint	(20°C HR: 60%): 30 min
Colours	Putty

SURFACE PREPAIRING**New surfaces**

- To clean all the strange product support and/or remainders.
- To apply on clean, dry, sandpaperings and taken the grease out of bottoms.
- To open to possible outcries or fissures until adjusted bottom and to eliminate remainders and produced dust.
- To apply so and as indicates in the sections Application.

Restoring and maintenance

- To eliminate old paintings by means of pickling or any other procedure, until healthy bottom.
- To come as in new supports.

Fecha de Alta

06-03-2008

Versión

5 - 03/03/2016

WAY OF USE

Application Notes

To mix both components in the suitable proportion. To mix only the amount to use during the time of life of the mixture.

To apply the product with a spatula.

You let dry.

To sandpaper in dry with grain sandpaper P-80 or P-240. Once sandpapering to come the painted one with the chosen painting.

T^a < 5 ° C polyester putties harden not

Solvent for dilution and cleaning

Cleaning: Dissolvent 1406

Way of use

Pallete / spatula

Aproximate dilution

0

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Old/New interior Wood			
MAX	Plasmont Metales	Imprimación Pintura de Acabado	Acropol, Montoepox
STD	Plasmont Metales	Imprimación Pintura de Acabado	Montosintético, Luxatín
Metal decoration			
MAX	Plasmont metales	Imprimación Pintura Acabado	Acropol, Montoepox
STD	Plasmont metales	Imprimación Pintura Acabado	Montosintético, Luxatín
Plastic			
MAX	Plasmont metales	Imprimación Pintura de Acabado	Acropol, Montoepox
STD	Plasmont metales	Imprimación Pintura de Acabado	Montosintético, Luxatín

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

Fecha de Alta

06-03-2008

Versión

5 - 03/03/2016

PACKINGS

1 Kg



FAMILY LINE

DESCRIPTION AND NATURE

Paste putty of two components, body type, with excellent anchorage on iron and metals, designed to cover defects and to equal surfaces before the painted one

USAGES

PROPERTIES

Elasticity
 Levelling
 Thixotropic
 Fast drying
 Base putty
 Fast sanding
 High filling power, given its high solids content.
 Good adhesion
 - Easy to sand
 Drying fast
 No cracking at all
 Good adhesion

TECHNICAL CHARACTERISTICS

Referencia Color	
Mixture relation	100 partes (masilla): 2-2.5 (Catalizador Masilla)
Finish	Matt
Aproximated performance by coat	Depending of product usage
Dry to touch	(20°C HR: 60%): 5-10 min
Dry to repaint	(20°C HR: 60%): 30 min
Colours	Putty

SURFACE PREPAIRING

New surfaces

- To clean all the strange product support and/or remainders.
- To apply on clean, dry, sandpaperings and taken the grease out of bottoms.
- To open to possible outcries or fissures until adjusted bottom and to eliminate remainders and produced dust.
- To apply so and as indicates in the sections Application.

Restoring and maintenance


- To eliminate old paintings by means of pickling or any other procedure, until healthy bottom.
- To come as in new supports.

Fecha de Alta

06-03-2008

Versión

5 - 03/03/2016



WAY OF USE

Application Notes

To mix both components in the suitable proportion. To mix only the amount to use during the time of life of the mixture.

To apply the product with a spatula.

You let dry.

To sandpaper in dry with grain sandpaper P-80 or P-240. Once sandpapering to come the painted one with the chosen painting.

T^a < 5 ° C polyester putties harden not

Solvent for dilution and cleaning

Cleaning: Dissolvent 1406

Way of use

Pallete / spatula

Aproximate dilution

0

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Old/New interior Wood			
MAX	Plasmont Metales	Imprimación Pintura de Acabado	Acropol, Montoepox
STD	Plasmont Metales	Imprimación Pintura de Acabado	Montosintético, Luxatín
Metal decoration			
MAX	Plasmont metales	Imprimación Pintura Acabado	Acropol, Montoepox
STD	Plasmont metales	Imprimación Pintura Acabado	Montosintético, Luxatín
Plastic			
MAX	Plasmont metales	Imprimación Pintura de Acabado	Acropol, Montoepox
STD	Plasmont metales	Imprimación Pintura de Acabado	Montosintético, Luxatín

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

PACKINGS

1 Kg