

Fecha de Alta

30-03-2007

Versión

12 - 27/02/2020



**FAMILY**      **TRATAMIENTOS DE LA MADERA**

**LINE**         **PROTECTORES AL AGUA (P. A.)**

### DESCRIPTION AND NATURE

Acrylic-urethane water-based primer. Excellent brushability, odourless. Great adhesion and excellent whiteness and coverage. Great filling capacity and easy to sand.

### USAGES

Outdoors/Indoors

Cement

Plaster

Wood

### PROPERTIES

Penetration power  
 No sanding necessary for repainting. Non expensive maintenance  
 Good adhesion  
 Drying fast  
 Odourless when dry  
 Good applicability

### TECHNICAL CHARACTERISTICS

Referencia Color	SELLADORA ACQUA BLANCA
Finish	Satin
Specific weight	1,44± 0,05 kg/l
Viscosity	45 +/- 5 PO
Solids in volume	38± 1
Solids in weight	58± 1
VOC	Cat. d/BA 150/130 (2007/2010):52,29 g/l
Aproximated performance by coat	7-10 m <sup>2</sup> /L
Dry to touch	(20°C HR 60%): 1 - 2 h. Sanding: 12-24h depending on yield
Dry to repaint	(20°C HR 60%):Mín 24 h
Colours	White

### SURFACE PREPARING

#### New surfaces

- Cement mortar, plaster and their derivatives:- Wait until completely set (minimum 30 days).
- Wait until they are completely dry.-The base must be free from foreign products and/or residue.
- Clean possible efflorescence from the base and neutralise alkaline surfaces.
- Use appropriate plaster to fill any defects in the base (to make a suitable selection, see the PREPARING BASES family for lines corresponding to powder plaster and prepared fillers).
- Treat mouldy bases with Montolimp.

#### New wood:

- Apply to woods with a moisture content of less than 12%.
- Sand down to remove any traces of glue in joints and milling defects.
- If the wood shows signs of ageing it must first be sanded down and any dust removed by brushing or other mechanical device.
- It is advised that you apply Montoxyl Fondo (code 1301) antioxidant primer.

Fecha de Alta

30-03-2007

Versión

12 - 27/02/2020

**Restoring and maintenance**

-Masonry and wood (plaster, cement and derivatives).

- If the wood has been varnished with Montoxyl, remove foreign products, remove any varnish that is loose or in poor condition, gently sand, remove the sanding dust and proceed as with new wood.

If varnished, remove this by stripping or by mechanical means and proceed as with new wood.

**WAY OF USE****Application Notes**

-Stir the product until evenly mixed.

-Apply according to the instructions set out in the attached application table.

-Do not apply the product at high temperatures or on surfaces exposed to strong sunlight.

-Ensure the area is well ventilated while the product is drying.

-Do not apply in relative humidity over 80%.

**Solvent for dilution and cleaning**

Water

Way of use	Aproximate dilution
Painting brush	0-10%
Roller	0-10%
Air-less gun	10-30%
Air-mix gun	10-30%

**SYSTEM****Procedures depending of surface type**

	Primer	Intermedium	Finish
<b>New work</b>			
<b>MAX</b>	Selladora Acqua	Selladora Acqua	Familia 1, 2 y 4 excepto acabados de 2 componentes
<b>STD</b>	Selladora Acqua		Familia 1, 2 y 4 excepto acabados de 2 componentes
<b>New wood indoor/outdoor</b>			
<b>MAX</b>	Al exterior: Anticarcomas Klearxyl Di	Selladora Acqua	Familia 1, 2 y 4 excepto acabados de 2 componentes, familia 5 al agua, Montoxyl Lasure Acqua Acabado pigmentado
<b>STD</b>	Al exterior: Anticarcomas Klearxyl Di	Selladora Acqua	Familia 1, 2 y 4 excepto acabados de 2 componentes, familia 5 al agua, Montoxyl Lasure Acqua Acabado pigmentado

**SECURITY**

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

**NOTE**

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

502343

# SELLADORA ACQUA BLANCA



Fecha de Alta

30-03-2007

Versión

12 - 27/02/2020

## PACKINGS

0.75 L, 4 L