

Fecha de Alta

28-06-2006

Versión

19 - 15/04/2024



FAMILY PAREDES Y TECHOS / SISTEMAS TINTOMÉTRICOS

LINE MATE

DESCRIPTION AND NATURE

Acrylic plastic paint that has excellent application, coverage and performance. Good white coverage and scrub resistance. Can be used outdoors in mild climates. This product contributes to LEED®, BREEAM® and VERDE certifications.

USAGES

Indoor / Outdoor in good weather
 Walls and ceilings
 Cement mortars
 Concrete
 Brick
 Plaster
 Dripping effect
 Drywall (gypsum plasterboard): fibreboard

PROPERTIES



- Gloss level: matt (according to UNE-EN 13300, at 85° reflectance < 10)

- Euroclasses certification as per norm UNE EN 13501-1:07:B-s1-d0

- Washability: Class 3 (according to Standard UNE-EN 13300)

Opacity: Class 1 for a performance of 5.5 m²/litre (according to Standard UNE-EN 13300). This information may vary depending on the colour chosen.

With anti-mould additive



TECHNICAL CHARACTERISTICS

Referencia Color	NEVADA+ BLANCO
Finish	.
Specific weight	1,56± 0,05 kg/l
Viscosity	115 +/- 15 PO
Solids in volume	43± 1
Solids in weight	65± 1
VOC	Cat. a/BA 75/30 (2007/2010):2,35 g/l
Aproximated performance by coat	11-13 m ² /L
Dry to touch	(20°C HR:60%):1h
Dry to repaint	(20°C HR:60%):3-4h
Colours	White

Fecha de Alta

28-06-2006

Versión

19 - 15/04/2024

Bases BLC, BL, TR, IN

SURFACE PREPAIRING

French norm DTU 59.1

New surfaces

Masonry mortar:

1. Wait for until forged total and drying of the surface (30 days minimum).
2. Clean the support of possible efflorescences by means of abrasive spurt
3. To neutralize alkaline surfaces.
4. In surfaces excessively polished to sandpaper to open the pore
5. Clean the strange product on support.
6. the suitable primer if necessary is Emulsion Fijadora or Fijamont.
7. Fill with powdered filler or prepared putties, (to see family 6)

Plaster:

1. Wait for until well dry (max, 20% humidity).
2. Eliminate rest of products and/or remainders.
3. Eliminate defects.
- 4 - Regulate the absorptions of the surface by means of primer.
- 5 - In surfaces excessively polished to sandpaper to open the pore.
- 6 - Fix the weak supports by means of suitable locking device (To see family 6).
- 7 - Fill with putty to eliminate the defects of the support (to see in family 6 - putties).

Plasterboard partition walls:

1. Carry out a general sanding of the joints and putty fixing areas.
2. Then, clean them to ensure the substrate is free of dust, grease and other contaminants.
3. For application on coloured boards that tend to generate stains, apply Monoplac Stain-Resistant Sealer.

Restoring and maintenance

1. Completely remove old paint that is in poor condition or that is poorly-adhered.
2. Glossy surfaces should be thinned out to ensure good adhesion.
3. On painted surfaces, check that the paint is solid and well-adhered. Its condition must be assessed, in order to avoid possible incompatibilities. Dust and dirt must also be eliminated before repainting.
4. Apply filler (Plasmont) to any defects on the surface.
5. Pre-treat mouldy walls using Montolimp.

WAY OF USE

Application notes

Shake product until perfectly homogenized.

First coat should be dilluted depending on surface conditon and porosity level.

Finish with one or more coats slightly dilluted until surface is totally covered.

Do not apply product at temperatures below 5° C or any surfaces which have been exposed to sunshine.

- Do not wash for the first 24 days.
- Never apply it outdoors if there is an imminent risk of rain, and avoid excessively wet days.
- Clean tools with water immediately after use.
- For spraying with Airless equipment, use 15 to 23 inch nozzles, pressure \approx 150 bar.

Solvent for dilution and cleaning

WATER

Way of use	Aproximate dilution
Painting brush	5-20%
Roller	5-20%
Air-less gun	5-30%
Air-mix gun	5-30%

Fecha de Alta

28-06-2006

Versión

19 - 15/04/2024

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Inner painted old work in good state			
MAX			
STD	Nevada+ Diluido		Nevada+
Inner painted old work in good state			
MAX	Eliminar + Fijador	Nevada+	Nevada+
STD	Eliminar + Nevada+		Nevada+
Project			
MAX	Fijador	Nevada+	Nevada+
STD	Nevada+ Diluido		Nevada+
Drywall (gypsum plasterboard)			
MAX	Nevada+ Diluido	Nevada+	Nevada+
STD	Nevada+ Diluido		Nevada+

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

15 L

Canned bases 0.75 L, 4 L, 12 L, 18.93 L