



**FAMILY** HTM  
**LINE** FACHADAS

## DESCRIPTION AND NATURE

Smooth economical coating, good whiteness, scrub resistance and opacity. For use in white work.

## USAGES

Outdoors/Indoors  
Cement mortars  
Facades  
Porous brick

## PROPERTIES

Waterproof  
Strong resistance to the atmospherical factors  
Does not spread flame  
Working smoothness  
Light & climatic resistant colours  
Does not present tacking  
Does not turn yellow  
Strong resistance to the atmospherical factors  
Does not spread flame  
Elasticity enough to resist the normal structural movements  
Easy application  
Does not turn yellow  
Water steam transpirable  
- AFNOR NFT 36005 Family I clase 7b2. COV=40 g/l. DTU 59.1 Clase D2 Norm p84-403 c - CLASSIFIED

## TECHNICAL CHARACTERISTICS

Referencia Color	HTM REVESTIMIENTO FACHADAS BLANCO
Finish	Smooth matt
Specific weight	1,62± 0,05 kg/l
Viscosity	124 +/- 15 PO
Solids in volume	46± 1
Solids in weight	68± 1
VOC	Cat. c/BA 75/40 (2007/2010):0,54 g/l
Aproximated performance by coat	4-8 m <sup>2</sup> /L
Dry to touch	(20° C HR: 60%): 30 min-1h. Washing: 25-30 days
Dry to repaint	(20° C HR: 60%): 4-6 h
Colours	White
	AFNOR NFT 36005 Familia I clase 7b2. COV=40 g/l. DTU 59.1 Clase D2 Norme P84-403

## SURFACE PREPAIRING

**French norm DTU 59.1**

### New surfaces

Cement mortar:

-Wait till complete drying of product (30 days minimum).

-Remove off any efflorescences by abrasive jet and neutralize alkaline surfaces.

Fecha de Alta

01-12-2010

Versión

4 - 12/04/2017

- Extremely polished surfaces should be sanpapered to open pores.
- Remove off any foreing products or remains.
- Cover surface imperfections with plaster or putty.

-Plaster:

- Wait till complete drying of product (20% max. Moisture level).
- Remove off any foreign product or product remains.
- Remove off any efflorescences.
- Use a sealant or matt paste to regulate surface absorption.
- Extremely polished surfaces should be sandpapered to open pore.
- Very damaged surfaces should be fixed with suitable product.
- Cover surface imperfections with plaster or putty.

### Restoring and maintenance

1. Remove off old paint completely.
2. Brilliant surfaces should be matted to ensure good adherence.
3. Check paint type and anchoring in painted surfaces to avoid incompatibilities. Remove off any dust or dirt before painting.
4. Cover surface imperfections with suitable putty of plaster.
5. Mildewed surfaces should be treated with fungicide.

## WAY OF USE

### Application Notes

Shake product until perfectly homogenized.

For the first coat application, this product should be dilluted depending on porosity and surface condition.

Finish with one or more coats slightly dilluted until surface is totally covered.

Do not apply product at temperatures below 5°C.

Do not apply in the sun or at extreme humid conditions.

### Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	10-20%
Roller	10-20%
Air-less gun	10-30%
Air-mix gun	10-30%
Glove	Al Uso
Aerographic gun	0-10%
Aerographic gun	10-30%
Low preasure turbo	0-10%
Low preasure turbo	10-30%
Flat brush	Al Uso

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>Support with mould</b>			
<b>MAX</b>	Fungicida + Fijador, Imprimación Fijadora	HTM revestimiento fachadas	HTM revestimiento fachadas
<b>STD</b>	Fungicida		HTM revestimiento fachadas
<b>Old paintings in bad state</b>			
<b>MAX</b>	Eliminar, Fijador, Imprimación Fijadora	HTM revestimiento fachadas	HTM revestimiento fachadas
<b>STD</b>	Eliminar, HTM revestimiento fachadas diluido		HTM revestimiento fachadas
<b>Old painting in good state</b>			

Fecha de Alta

01-12-2010

Versión

4 - 12/04/2017

<b>MAX</b>	HTM revestimiento fachadas diluido	HTM revestimiento fachadas	HTM revestimiento fachadas
<b>STD</b>	HTM revestimiento fachadas diluido		HTM revestimiento fachadas

### Support weak

<b>MAX</b>	Fijador, Imprimación Fijadora	HTM revestimiento fachadas	HTM revestimiento fachadas
<b>STD</b>	HTM revestimiento fachadas diluido		HTM revestimiento fachadas

### Masonry mortar

<b>MAX</b>	Fijador, Imprimación Fijadora	HTM revestimiento fachadas	HTM revestimiento fachadas
<b>STD</b>	HTM revestimiento fachadas diluido		HTM revestimiento fachadas

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

## PACKINGS

4 L, 12 L