

UNO BARNIZ LADRILLO SATINADO


FAMILY ANTIHUMEDAD E IMPERMEABILIZAC.

LINE IMPERMEABILIZACION VERTICAL

DESCRIPTION AND NATURE

Protective water repellant varnish for porous surfaces. Transparent. Avoid excess of product which leads to the build-up of film .

USAGES

Outdoors/Indoors

Brick

Stone

Exposed brickwork

Fibre-cement

Cement mortars

PROPERTIES

Waterproof

Does not alter support tone once dry

Do protect the varnished surfaces from atmospherical factors

To fix the dusty surfaces

Porosity regulator

Does not spread flame

Satinado

TECHNICAL CHARACTERISTICS

Referencia Color	UNO BARNIZ LADRILLO SATINADO
Finish	Satin
Specific weight	0,98 ± 0,05 kg/l
Viscosity	37 +/- 8 SG
Solids in volume	17 ± 1
Solids in weight	19 ± 1
VOC	Cat. c/BA 75/40 (2007/2010):38,84 g/l
Aproximated performance by coat	9-15 m ² /L
Dry to touch	(20°C HR 60%): 30 min -1 h
Dry to repaint	(20°C HR 60%): 8h
Colours	Transparent

SURFACE PREPAIRING
New surfaces

- Remove off any efflorescences, remains or foreign products by abrasive jet and neutralize alkaline surfaces.
- Extremely polished surfaces should be sanpapered to open pores.
- Cover surface imperfections with suitable plaster.
- Mildewed surfaces should be treated with Montolimp.

Restoring and maintenance

- 1.This product should only be applied on surfaces free of any paint trace and with open porous.
- 2.For old surfaces that comply with these requirements, proceed as per new surfaces.

UNO BARNIZ LADRILLO SATINADO

WAY OF USE

Application Notes

-Shake product until perfectly homogenized.

-Thinning: 3/5 parts of water per 1 part BARNIZ LADRILLO SATINADO. The bigger the porous, is the less thinning needs. Excess of product may cause glossy areas.

-This product should not be applied at temperatures below 5° or any surfaces which have been in the sun.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	3 a 5 partes de agua 1 de barniz
Roller	3 a 5 partes de agua 1 de barniz
Air-less gun	3 a 5 partes de agua 1 de barniz
Air-mix gun	3 a 5 partes de agua 1 de barniz
Aerographic gun	3 a 5 partes de agua 1 de barniz
Low pressure turbo	3 a 5 partes de agua 1 de barniz

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Support with mould			
MAX	Montolimp	Uno Barniz Ladrillo satinado	Uno Barniz Ladrillo satinado + Montoplás
STD	Montolimp		Uno Barniz Ladrillo satinado + Montoplás
Artificial stone, bricks , and porous roofing tiles			
MAX	Uno Barniz Ladrillo Satinado		Uno Barniz Ladrillo Satinado
STD	Uno Barniz Ladrillo Satinado		Uno Barniz Ladrillo Satinado
Old paintings in bad state			
MAX	Eliminar antiguas pinturas	Uno Barniz Ladrillo Satinado	Uno Barniz Ladrillo Satinado
STD	Eliminar antiguas pinturas		Uno Barniz Ladrillo Satinado
Brickwork			
MAX	Uno Barniz Ladrillo Satinado		Uno Barniz Ladrillo Satinado
STD	Uno Barniz Ladrillo Satinado		Uno Barniz Ladrillo Satinado
Support weak			
MAX	Fijamont, Emulsión Fijadora	Uno Barniz Ladrillo Satinado	Uno Barniz Ladrillo Satinado
STD	Fijamont, Emulsión Fijadora		Uno Barniz Ladrillo Satinado
Masonry mortar			
MAX	Fijamont, Emulsión Fijadora	Uno Barniz Ladrillo Satinado	Uno Barniz Ladrillo Satinado
STD	Uno Barniz Ladrillo Satinado		Uno Barniz Ladrillo Satinado

SECURITY

UNO BARNIZ LADRILLO SATINADO

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 4 L, 12 L