503247

Fecha de Alta 01-08-2006 Versión

CONVERPLUS ANTISILICONAS



3 - 16/05/2016



FAMILY PRODUCTOS PARA USO ESPECIFICO

LINE ADITIVOS

DESCRIPTION AND NATURE

Silicone oil in solution form, to be added to MONTO manufactured pigmented and transparent solvent based paints. Specifically formulated to prevent the forming of cracking and other superficial faults or imperfections.

USAGES

Outdoors/Indoors

Designed to eliminate surface defects due to poor paint levelling, such as craters, fish-eyes or wrinkles, caused by a contaminating undercoat.

Designed to restore painted surfaces that have been contaminated with silicone oil or silicones

Designed to eliminate poor levelling caused by the evaporation of solvents.

Designed to eliminate "overspray" in paint gun applications.

In solvent-based paints

PROPERTIES

Reduce the surface tension

Reduce the inter-coats tension

Improves the tension balance between products with different polarity

Hides superficial defects as crates, fringes, orange skin appearance...

Hides defects caused by an inusual velocity dryness due to extreme solvent evaporation

Hides defects caused by high temperatures application which provokes an excessive solvent evaporation

TECHNICAL CHARACTERISTCS		
Referencia Color	CONVERPLUS ANTISILICONAS	
Mixture relation	1-2% en volumen respecto a la pintura a aditivar	
Finish	Base painting	
Specific weight	0,84± 0,05 kg/l	
Solids in volume	4± 1	
Solids in weight	5± 1	
Aproximated performance by coat	Depending of product usage	
Dry to touch	(20°C HR: 60%): As per product to be added to.	
Dry to repaint	(20°C HR: 60%): As per product to be added to.	
Colours	Colorless	

SURFACE PREPAIRING

New surfaces

As per product to which is to be added. This product should only be added at the top coat phase.

Restoring and maintenance

As per product to which is to be added. This product should only be added at the top coat phase.

WAY OF USE

Application Notes

- -This product should only be added those products indicated under recommended applications section.
- -Paint or varnish to which this product is to be added should be perfectly homogenized.

503247

Fecha de Alta 01-08-2006 Versión

CONVERPLUS ANTISILICONAS



3 - 16/05/2016

- -Follow recommended addition proportions indicated under application systems section.
- -Mixture of varnish/paint + converplus antisilicona should be perfectly homogenized.
- -This product should only be added at the top coat process.

Solvent for dilution and cleaning

1405

Way of use Aproximate dilution

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish	
On usualy surfaces				
MAX STD	Idem que los productos a los que se	Idem que los productos a los que se	Producto de acabado	
0.5	adiciona	adiciona	Troducto do dodedado	

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time: 18 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adecuate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.125 L, 0.75 L