

Fecha de Alta

26-06-2007

Versión

11 - 21/07/2020


FAMILY ESMALTES / SISTEMAS TINTOMÉTRICOS

LINE LINEA MONTOMIX

DESCRIPTION AND NATURE

Synthetic glycerophthalic pigmented gloss enamel, recommended in alkyd systems on steel, wood or plasterwork.

USAGES

Outdoors/Indoors

Iron

In order to apply on galvanized iron to consult with the technical department

PROPERTIES

- Makes a film
- Penetration power
- Strong resistance to the atmospherical factors
- With micronic pigments wich are UV protectives
- No cracking at all
- Does not form blisters
- Odourless when dry
- Good applicability

TECHNICAL CHARACTERISTICS

Referencia Color	MARISMA BRILLANTE BASE IN
Finish	Gloss
Specific weight	1 ± 0,05 kg/l
Viscosity	75 +/- 5 KU
Solids in volume	25 ± 1
Solids in weight	41 ± 1
VOC	Cat. d/BD 400/300 (2007/2010): 288,47 g/l
Aproximated performance by coat	12-14 m ² /L
Dry to touch	(20°C HR: 60%): 2-4 h
Dry to repaint	(20°C HR: 60%): 24 h
Colours	TR, IN, BL base. Colora and Montomix tintometric system

SURFACE PREPAIRING
New surfaces

New wood surfaces:

1. The surface must be free from other products and/or residues.
2. Apply to wood with a moisture content of less than 20%.
3. Apply to wood in good condition, grease and dust free, and dry.
4. Sand down to remove any traces of glue in joints and milling defects.
5. If the wood shows signs of ageing, it should first be sanded down, primed and any dust removed by brushing or any other mechanical means.
6. In this case the most suitable primer is Selladora Sellalux.

Iron and derivatives:

1. To protect the surface, before painting, treat with suitable primers (family 6) following the specifications given on the card.
2. The surface to be painted must be free of other products and/or residues, grease and dust free, and dry. Any signs of rust should be removed by brushing or any other mechanical means. Oxifin is also suitable (see technical specifications).

Fecha de Alta

26-06-2007

Versión

11 - 21/07/2020

Plasterwork (plaster, cement and derivatives):

1. Treat these surfaces in the usual way, removing saltpetre, excess moisture and efflorescence.
2. Remove other products and/or residues.
3. Once dry, prime with Sellalux Primer.

Restoring and maintenance

Varnished or painted wood:

1. If varnished with Montoxyl colour: remove other products, remove any varnish which is flaking or in bad condition, sand gently, remove sanding dust and proceed as for new wood.
2. If varnished, strip using Quitamont Gel or by mechanical means and proceed as for new wood.
3. If they have been coated with a synthetic enamel (Montosintético, Marisma, Luxatín or similar), open the pore by sanding down, remove the resulting dust and proceed as with new wood.

-Enamelled iron and derivatives:

1. On paintwork in good condition, sand to roughen the surface, checking that the paint is not loose.
2. On paintwork in bad condition, remove by mechanical or chemical means and proceed as for new surfaces.

WAY OF USE**Application notes**

Stir the product until perfectly blended.

-Apply according to the instructions in the attached application table.

-New wood should first be primed using Montoxyl Fondo (cod. 1301) if you wish to protect it against fungus or bacteria.

-Do not apply the product in extreme temperatures, or to surfaces exposed to strong sunlight.

-Keep the space well ventilated while the product is drying.

- Do not apply with relative moisture over 80%.

Solvent for dilution and cleaning

Disolvente 1401, o Simil Aguarrás

Way of use**Aproximate dilution****SYSTEM****Procedures depending of surface type**

	Primer	Intermedium	Finish
New work			
MAX			
STD	Montoxyl fondo	Selladora Sellalux o Selladora Acqua Blanca	Marisma brillante
Metal			
MAX			
STD	Impriepox M-10, Impripol, Minio Blanco, Imprim. Antioxidante, Imprim. Industrial	Impriepox M-10, Impripol, Minio Blanco, Imprim. Antioxidante, Imprim. Industrial	Marisma brillante
Wood			
MAX			
STD	Selladora Sellalux o Selladora Acqua Blanca	Selladora Sellalux o Selladora Acqua Blanca	Marisma brillante

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Fecha de Alta

26-06-2007

Versión

11 - 21/07/2020

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 4 L