

CREA BARNIZ ULTRA BRILLANTE



FAMILY

CREA

LINE

MADERA INTERIOR

DESCRIPTION AND NATURE

Aliphatic acrylic-urethane varnish for protecting and decorating interior/exterior wood. Resistant to UV rays. Can be applied on flooring, parquet, furniture, windows, etc.. With nano additives, it creates a waterproof layer that is highly durable and resistant to impact, abrasion and wear and tear. Brings out the wood's grain. Very easy to apply and low odour.

USAGES

Exterior with protection.

Indoors

Indoors

Wood

Recommended previously created with primer

Suitable for furniture and doors

Suitable for parquet and wooden floors

Apply a maximum of 110 +/- 20 g/m2 per coat.

Use of clean wood

Resistance to extreme climates

PROPERTIES

Strongness

Waterproof

Surface protection

Odourless when dry

Resistance to friction and hits

Anti-dust

Washable

Easily applicable

- Water-based

Drying fast

TECHNICAL CHARACTERISTICS

Referencia Color CREA BARNIZ ULTRA BRILLANTE INCOLORO

Finish Gloss

Specific weight 1,05± 0,05 kg/l

Viscosity 55 +/- 5 SG

Solids in volume 1± 1

Solids in weight 26± 1

VOC Cat. i/BA 140/140 (2007/2010): 66,56 g/l

Aproximated performance by coat 6-9 m²/L

Dry to touch 30 - 60 min.

Dry to repaint 12 - 24 h.

Colours Colorless

SURFACE PREPARING

New surfaces

New woods.

The surface must be free from foreign products and/or residues.

CREA BARNIZ ULTRA BRILLANTE

Apply over wood with less than 20% moisture content.

Apply to healthy, grease-free, dust-free, dry wood.

Sand down to remove any traces of glue in joints and milling defects.

If the wood shows signs of ageing it must first be sanded down and any dust removed by brushing or other mechanical means.

Restoring and maintenance

Varnished or painted wood:

If they were varnished with open-pore wood stains: remove foreign products, remove any loose or peeling varnish, lightly sand, remove dust from sanding and proceed as on new woods.

- If they were varnished with closed-pore varnishes, sand deeply and if necessary remove by stripping with chemical or mechanical means and proceed as on new woods.

- If they were varnished with cellulose or polyurethane varnishes, remove by stripping with chemical or mechanical means and proceed as on new woods.

- If they were painted with synthetic enamels, remove by stripping by chemical or mechanical means, sand down to wood and proceed as on new woods.

WAY OF USE

Application Notes

Stir the product until evenly mixed.

Apply on clean and dry substrates.

Apply following the recommended dilutions as described in the Application Systems section.

Sand before application to ensure good penetration and smooth finish on the wood.

Do not apply the product at high temperatures or on surfaces exposed to strong sunlight.

Ensure the area is well ventilated while the product is drying.

Do not apply with relative humidity over 80%.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	0 - 10%
Roller	0 - 20 %
Spray gun	0 - 20 %

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
New wood indoor/outdoor			
MAX	Crea impregnante Incoloro/Color	Crea Barniz Ultra Brillo/Satinado/Mate	Crea Barniz Ultra Brillo/Satinado/Mate
STD	Crea impregnante Incoloro/Color		Crea Barniz Ultra Brillo/Satinado/Mate
varnished or painted wood outdoor/indoor			
MAX	Decapar+Crea Impregnante Incoloro/Color	Crea Barniz Ultra Brillo/Satinado/Mate	Crea Barniz Ultra Brillo/Satinado/Mate
STD	Decapar+Crea Impregnante Incoloro/Color		Crea Barniz Ultra Brillo/Satinado/Mate

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

CREA BARNIZ ULTRA BRILLANTE

NOTE

Maximum recommended storage time : 0 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.5 L, 2.5 L